



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
15.09.2004 Bulletin 2004/38

(51) Int Cl.7: **C09K 11/06**, C07D 487/04,
C09B 57/12

(21) Application number: **98907969.4**

(86) International application number:
PCT/EP1998/000314

(22) Date of filing: **21.01.1998**

(87) International publication number:
WO 1998/033862 (06.08.1998 Gazette 1998/31)

(54) **FLUORESCENT MATERIALS AND THEIR USE**

FLUORESZIERENDE MATERIALIEN UND IHRE ANWENDUNG

MATERIAUX FLUORESCENTS ET LEUR UTILISATION

(84) Designated Contracting States:
**AT BE CH DE DK ES FI FR GB GR IE IT LI NL PT
SE**

(30) Priority: **03.02.1997 EP 97810049**
03.02.1997 EP 97810050
03.02.1997 EP 97810051
04.02.1997 EP 97810054
04.02.1997 EP 97810055

(43) Date of publication of application:
05.01.2000 Bulletin 2000/01

(73) Proprietor: **Ciba Specialty Chemicals Holding Inc.**
4057 Basel (CH)

(72) Inventors:

- **OTANI, Junji**
Kobe-shi, Hyogo 657 (JP)
- **KUNIMOTO, Kazuhiko**
Takatsuki-shi, Osaka 569-11 (JP)
- **DENO, Takashi**
Nishinomiya-shi, Hyogo 669-11 (JP)
- **DEVLIN, Brian, Gerrard**
4053 Basel (CH)
- **KODAMA, Kunihiko**
Chitose-shi, Hokkaido 066 (JP)

(56) References cited:

EP-A- 0 456 609 **WO-A-94/15441**
GB-A- 2 292 947

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to a composition comprising (a) an effective amount of a guest chromophore embedded in a matrix of a host chromophore, or (b) a host chromophore and an effective amount of a guest chromophore both embedded in a polymer matrix, wherein the absorption spectrum of the guest chromophore overlaps with the fluorescence emission spectrum of the host chromophore, and wherein the host chromophore is selected from the group consisting of benzo [4,5] imidazo [2,1-a] isoindol-11-ones.

[0002] Further, the present invention relates to a process for the preparation of this composition, a polymerisable composition comprising this composition, a composition comprising a carrier material with a high relief of a polymerized photoresist material containing this composition, a process for the preparation of fluorescent high relief images on a carrier, the use of the compositions as fluorescent materials, especially in electroluminescent devices, and novel non-functionalized benzo[4,5]imidazo[2,1-a] isoindol-11-one derivatives.

[0003] Combinations comprising host chromophores with guest chromophores dissolved therein to generate materials with enhanced fluorescence and large differences between absorption maximum and emission maximum are highly desired materials that possess a wide range of potential and actual technical applications. The large difference between the absorption (excitation) maximum and the emission maximum is due to the occurrence of resonant energy transfer between the respective host and guest chromophores.

[0004] The possibility of energy transfer between chromophores that possess an area of overlap of the absorption spectrum of a guest chromophore with the fluorescence emission spectrum of a host is known. For example, H. Port et al. describe in Z. Naturforsch., 36a, pages 697 to 704 (1981) mixed crystals of fluorene doped with dibenzofurane or benzindan with an enhanced fluorescence in the UV region at temperatures below 100K. However, the low temperature fluorescence has no practical value and is only of scientific interest.

[0005] C.W. Tang et al. disclose in J. Appl. Phys., 65, 3610 to 3616 (1989) a multilayered electroluminescent device with a light emitting layer composed of 8-hydroxyquinoline aluminum, in which is embedded a zone doped with a fluorescent molecule such as coumarin. The device shows improved electroluminescence and an effective Stoke's color shift which is dependent on the particular dopant. The manufacture of the device is complicated and not readily suitable for an industrial production.

[0006] J. M. Lang et al. describe in J. Phys. Chem. 97, pages 5058 to 5064 (1993) the combination of coumarin as host and rhodamine as guest whereby both components are dissolved in polyacrylic acid, but Lang's study demonstrates enhanced fluorescence only under high pressure.

[0007] In WO 93/23492 are disclosed fluorescent microparticles with an enhanced Stokes shift, which are composed of soluble and fluorescent host and guest dyes absorbed or bonded to polymeric microparticles. The material is used for the optical detection of nucleic acids like DNA or RNA. Unfavorably, the solid state fluorescence of these microparticles is poor.

[0008] US 5,227,252 discloses a fluorescent composition of 8-hydroxyquinoline aluminum as host and quinacridones as guest. Similarly, JP-A-05 320 633 discloses a fluorescent composition of 8-hydroxyquinoline aluminum as host and diketopyrrolopyrroles as guest. However, in both documents, the guests are insoluble materials, they are dissolved mainly as micro-sized clusters. The occurrence of micro-sized clusters is due to co-sublimation processes being the means of preparation. The materials possess a larger Stoke's shifts than would be anticipated by normal single component fluorescent materials, and are used for example as light emitting materials in electroluminescent devices. The process for their manufacture requires large expenditures on technical equipment to ensure the careful control process conditions such as vacuum and temperature, to achieve the desired mixed material. The process is not convenient for large scale industrial manufacture.

[0009] In EP-A-0 456 609 is disclosed a process for the preparation of 1,2,3,4-tetrachloro-benzo[4,5] imidazo[2,1-a] isoindol-11-one and its derivatives in the presence of selected solvents. These compounds are pigments showing solid state fluorescence and improved outdoor durability. It is also mentioned therein, that the combination of 95% of the yellow 1,2,3,4-tetrachloro-benzo[4,5] imidazo[2,1-a]isoindol-11-one with 5% of Indanthrone Blue generates a green fluorescent pigment. Hence, such a system is a pigment composite, wherein the new color generated is simply a sum of the two component colors. The color is not created by virtue of the occurrence of complex, molecular level, energy transfer processes that require close interaction between the components of the mixture.

[0010] F.W. Harris et al. describe in ACS Symp. Ser. 132, 39 (1980) the compound 1,2,3,4-tetraphenyl-benzo [4,5] imidazo [2,1-a] isoindol-11-one as a model material, as a part of their investigations into phenylated polyimidazopyrrolones for potential use in aerospace applications. However, no reference to its fluorescence behavior is made.

[0011] Hence, the object of the invention on hand was to find a fluorescent composition, which does not show the above mentioned disadvantages, preferably a composition should be provided which

- has a greatly enhanced and intense fluorescence emission,

- shows an intense solid state fluorescence, wherein the emission spectrum is preferably in the visible region of the electromagnetic spectrum,
- is excitable using wavelengths in both the UV and visible regions,
- shows a very excellent photostability and outdoor durability,
- 5 - shows a wide range of emission spectra through selection of suited guest molecules (color tuning),
- has a high thermal stability,
- is easily prepared, i.e. by a (co-)precipitation process,
- can be used for the preparation of electroluminescence devices,

10 if the host chromophore is selected from the group consisting of benzo[4,5]imidazo[2,1-a]isoindol-11-ones, which means derivatives of benzo[4,5]imidazo[2,1-a]isoindol-11-one of formula (V) or (VIa) as the fundamental substance.

[0012] In addition, the enhancement factor for the present compositions preferably should be all positive and should be at least 1.3, more preferably at least 2 and most preferably at least 5. The term "enhancement factor" as used herein, is defined as the increased or decreased factor, in terms of peak height emission intensities of a solid-state
15 powder comprising of host and guest fluorescent moieties compared to an identical powder that does not contain any fluorescent guest moieties. Comparisons are considered real, for as long as the excitation radiation wavelengths are identical. In general, the emission wavelengths of host/guest material occur at longer wavelengths (lower energy) as compared to an identical material with no guest component.

[0013] Accordingly, a composition was found comprising (a) an effective amount of a guest chromophore embedded in a matrix of a host chromophore, or (b) a host chromophore and an effective amount of a guest chromophore both
20 embedded in a polymer matrix, wherein the absorption spectrum of the guest chromophore overlaps with the fluorescence emission spectrum of the host chromophore, and wherein the host chromophore is selected from the group consisting of benzo[4,5]imidazo[2,1-a]isoindol-11-ones of formula (II) or (VIa).

[0014] In addition, a process for the preparation of this composition, a polymerizable composition comprising this
25 composition, a composition comprising a carrier material with a high relief of a polymerized photoresist material containing this composition, a process for the preparation of fluorescent high relief images on a carrier, the use of the compositions as fluorescent materials, esp. in electroluminescent devices, and novel non-functionalized benzo[4,5]imidazo[2,1-a]isoindol-11-one derivatives were found, too.

[0015] A first embodiment of the present invention relates to a composition comprising (a) an effective amount of a
30 guest chromophore embedded in a matrix of a host chromophore, or (b) a host chromophore and an effective amount of a guest chromophore both embedded in a polymer matrix, wherein the absorption spectrum of the guest chromophore overlaps with the fluorescence emission spectrum of the host chromophore, and wherein the host chromophore is selected from the group consisting of benzo[4,5]imidazo[2,1-a]isoindol-11-ones of formula (V) or (VI a).

[0016] The host chromophore is selected from the group consisting of derivatives of benzo[4,5]imidazo[2,1-a]isoindol-11-one and benzo[4,5]imidazo[2,1-a]isoindol-11-one of formula (V) or (VI a) (hereinafter referred to as benzoimidazoisoindolone(s)) itself. The compounds are preferably derivatives that are soluble in an organic or aqueous solvent.

[0017] Under the aspects of the invention solubility of host chromophores means preferably that at least 10 mg, more preferably at least 50 mg and most preferably at least 100 mg of the benzoimidazoisoindolone derivative are soluble
40 in 1 liter of solvent like dimethylformamide, at 20°C. It is self-evident, that the solubilities are higher at increasing temperatures and depend on the choice of a solvent.

[0018] In one embodiment of this invention, the guest chromophore preferably is soluble, at least to some extent, in a solvent, and - if desired - in the host chromophore, allowing formation of homogeneous solid solutions.

[0019] Solubility of a guest chromophore means in the context of the invention that at least 200 mg, more preferably at least 300 mg and most preferably at least 500 mg of the guest chromophore are soluble in 1 liter of solvent like
45 dimethylformamide at 20 °C. This definition employs also to compositions where the host and guest chromophores are embedded in a polymer matrix.


[0020] The guest chromophore is selected from the group consisting of quinacridones, perylenes, perinones, diketo- and dithioketopyrrolopyrroles, rhodamines, coumarins, xanthenes, oxazines, oxazoles, cyanines, phthalocyanines, porphyrines, styryl dyes, metal complexes and mixtures thereof.

50 [0021] Preferred guest chromophores are selected from group consisting of quinacridones, perylenes, perinones, diketopyrrolopyrroles, rhodamines, coumarins, cyanines, phthalocyanines, porphyrines, styryl dyes and mixtures thereof. Especially preferred are quinacridones, perylenes, diketopyrrolopyrroles, rhodamines, coumarins and mixtures thereof.

[0022] The guest compounds and their derivatives are well known in the art or can be prepared by analogous processes.
55

[0023] Quinacridones can be found described in Chemical Reviews 67 (1) pages 1 to 18 (1967).

[0024] The quinacridones may correspond to the formula VII




(VII),

wherein


R₂₆ to R₂₉ and R₃₂ to R₃₅ independently from one another can be H, C₁ to C₆alkyl, C₁ to C₆alkoxy, F, Cl, Br, CN, NO₂, or -NR₂₁R₂₂, wherein R₂₁ and R₂₂ independently from one another are H, C₁ to C₂₀alkyl, phenyl, C₁ to C₁₂alkylphenyl, benzyl or C₁ to C₁₂alkylbenzyl, or R₂₁ and R₂₂ together mean tetramethylene, pentamethylene or -CH₂CH₂-O-CH₂CH₂-; or two neighbored residues of R₂₆ to R₂₉ and/or R₃₂ to R₃₅ together with carbon atoms, to which they are linked, a 5- or 6-membered aliphatic, heteroaliphatic, aromatic or heteroaromatic ring, whereby the heteroatoms are selected from the group of -O-, -S- and N; and

R₃₀ and R₃₁ independently from one another are H, C₁ to C₁₈alkyl, C₂ to C₁₈alkenyl, C₂ to C₁₈alkinyl, phenyl, benzyl, C₁ to C₆alkylphenyl, C₁ to C₆alkylbenzyl or R₃₆-O-C(O)-, wherein R₃₆ means C₁ to C₁₈alkyl, C₂ to C₁₈alkenyl, C₂ to C₁₈alkinyl, phenyl, benzyl, C₁ to C₆alkylphenyl, or C₁ to C₆alkylbenzyl.

[0025] Perylenes can be found described in US-A-4 446 324 and US-A-5 470 502. Preferred examples are those perylenes of formulae IX and X,



(IX),



(X),


wherein

R₃₇ and R₃₈ independently from one another can be F, Cl, Br, or CN,


R₃₉ and R₄₀ independently from one another mean R₃₆-O-C(O)-, wherein R₃₆ means C₁ to C₁₈alkyl, C₂ to C₁₈alkenyl, C₂ to C₁₈alkinyl, phenyl, benzyl, C₁ to C₆alkyl phenyl, or C₁ to C₆alkylbenzyl.

R₄₁ and R₄₂ independently from one another can be H, C₁ to C₁₈alkyl, C₂ to C₁₈alkenyl, C₂ to C₁₈alkinyl, phenyl, benzyl, C₁ to C₆alkylphenyl, C₁ to C₆alkylbenzyl or R₃₆-O-C(O)-, wherein R₃₆ means C₁ to C₁₈alkyl, C₂ to C₁₈alkenyl, C₂ to C₁₈alkinyl, phenyl, benzyl, C₁ to C₆alkylphenyl, or C₁ to C₆alkyl benzyl, and the R₄₃ independently from one another are C₁ to C₁₈alkoxy, phenoxy or C₁ to C₁₂alkylphenoxy.


[0026] Some examples of the commercially available compounds are shown;



(Lumogen F Yellow),




(Lumogen F Orange),



(Lumogen F Red).

Diketo- and dithioketopyrrolopyrroles can be found described in US-A-4 415 685 and JP-A-61 162 555.

[0027] Examples for diketopyrrolopyrroles correspond to the formula XI,



(XI),


wherein

the R_{44} independently from one another are H, halogen, or phenyl which is unsubstituted or substituted with C_1 to C_6 alkyl, C_1 to C_6 alkoxy, phenyl, C_1 to C_4 alkylphenyl, F, Cl, Br, CN, NO_2 , or $-NR_{21}R_{22}$, wherein R_{21} and R_{22} independently from one another are H, C_1 to C_{20} alkyl, phenyl, C_1 to C_{12} alkylphenyl, benzyl or C_1 to C_{12} alkylbenzyl, or R_{21} and R_{22} together mean tetramethylene, pentamethylene or $-CH_2CH_2-O-CH_2CH_2-$; and

the R_{45} independently from one another mean H, C_1 to C_{18} alkyl, C_2 to C_{18} alkenyl, C_2 to C_{18} alkinyl, phenyl, benzyl, C_1 to C_6 alkyl phenyl, or C_1 to C_6 alkylbenzyl, or $R_{30}-O-C(O)-$, wherein R_{30} means C_1 to C_{18} alkyl, C_2 to C_{18} alkenyl, C_2 to C_{18} alkinyl, phenyl, benzyl, C_1 to C_6 alkylphenyl, or C_1 to C_6 alkyl benzyl.

[0028] A range of commercial rhodamines are available from ACROS ORGANICS catalogue of fine chemicals Vol. 1 (1996).

[0029] Preferred examples of rhodamines are those of the formula XII,



(XI),

wherein

wherein R_{21} and R_{22} independently from one another are H, C_1 to C_{20} alkyl, phenyl, C_1 to C_{12} alkylphenyl, benzyl or C_1 to C_{12} alkylbenzyl, or R_{21} and R_{22} together mean tetramethylene, pentamethylene or $-CH_2CH_2-O-CH_2CH_2-$;

R_{46} means H, C_1 to C_{18} alkyl, C_2 to C_{18} alkenyl, C_2 to C_{18} alkinyl, phenyl, benzyl, C_1 to C_6 alkyl phenyl, or C_1 to C_6 alkylbenzyl, or an equivalent of a metal or ammonium cation;

and R_{47} means the group $=NR_{48}$, or the group $=NR_{48}R_{49}X$, R_{48} and R_{49} independently from one another are H, C_1 to C_{18} alkyl, phenyl, C_1 to C_{12} alkylphenyl, benzyl or C_1 to C_{12} alkylbenzyl; and X is monovalent anion.

[0030] A range of commercial coumarins, oxazines, cyanines, xanthenes and styryl dyes are available from ACROS ORGANICS catalogue of fine chemicals Vol. 1 (1996).

A range of commercial oxazoles are available from DOJINDO LABORATORIES catalogue 18th edition (1992).

[0031] Porphyrines and phthalocyanines are for example described in a book "The Phthalocyanines" (Frank H. Moser et. al., published by Franklin, 1983).

[0032] In the context of the invention, effective amount of a guest chromophore means for example, that the composition may contain from 0.001 to 30, preferably from 0.01 to 20, more preferably from 0.01 to 10 and most preferably from 0.01 to 5 percent by weight, of guest chromophore, related to the total amount of host and guest chromophore.

[0033] Further, in the context of this invention, the meaning of the overlap of the absorption spectrum of the guest chromophore with the fluorescence emission spectrum of the host chromophore, is clear to a skilled person in this field. However, to facilitate the understanding to others, overlap means "spectral overlap" defined by the following integral

$$S = \int_0^{+\infty} f_F(v) f_A(v) dv$$

wherein $f_F(v)$ is normalized, so that $\int_0^{+\infty} f_F(v) dv$ is equal to fluorescence quantum yield of the host, and where v is the wave number, f_F the fluorescence spectrum of the host measured in quanta, and f_A the spectral distribution of the molar extinction coefficient of the guest. The spectral overlap to realize photoluminescence enhancement usually is greater than 10, preferably greater than 100, more preferably greater than 500. An upper limit makes no sense, because the quantity "overlap" has no maximum (i.e. the larger, the better).

[0034] In the context of this invention, embedded means a distribution of the guest chromophore (or both host and guest chromophore, if a polymer matrix is used) within the matrix or total amount of host chromophore (or - accordingly, of course, the polymer matrix). Preferably, this distribution is homogeneously. Hence, in another preferred embodiment of this invention, (a) the guest chromophore is homogeneously distributed within the matrix of the host chromophore, or (b) the host chromophore and the guest chromophore both are homogeneously distributed within the polymer matrix.

[0035] In the context of this invention, the term "homogeneously" means that the components within the matrix, e. g. the guest chromophore, is evenly or uniformly distributed or dispersed throughout the matrix (or host or host/polymer matrix), and, preferably in the ideal case are essentially equidistant from each other. According to observations today, the more even or uniform the distribution is, the better are the fluorescence properties, because the coexistence of

areas having bright and weak fluorescence are reduced as well as areas wherein the emission color is closer to that of the host than the guest. Furthermore, a homogeneous or even distribution is preferred, because usually the chances for aggregation are decreased.

[0036] In another preferred embodiment of this invention, the average particle size of the guest chromophores (or the host and guest chromophores, if a polymer matrix is applied) are not bigger than a desired diameter, preferably more than a desired amount of the guest chromophores (or host and guest chromophores, if a polymer matrix is applied) are in their molecular state. Most preferably, the guest chromophores (or host and guest chromophores, if a polymer matrix is applied) are molecularly dissolved and homogeneously distributed within the matrix of the host chromophore (or the polymer matrix).

[0037] In the context of this invention, the term "dissolved" means that a molecule exists as a free and isolated entity in a given matrix, preferably in such a way, that it is disengaged from any interactions between molecules of the same species, i.e. it is entirely surrounded by matrix molecules. Usually the matrix can be a liquid organic solvent or a solid material such as a polymer or another fluorescent material (host), which possesses a different chemical structure. The concentration limits for molecules in the dissolved state in general depend strongly on the associative nature between the molecule and the matrix medium, and/or the intrinsic cohesive forces that exist between the guest molecules in question. Correspondingly, it is impossible to define universal ranges for preferred concentrations, and therefore, usually must be treated on an ad hoc basis, e.g. by a few simple experiments.

[0038] Polymers which may be used as polymer matrix may be selected from thermoplastics, polymer blends, thermosettings and structurally crosslinked polymers. The polymers may be homopolymers, copolymers, blockpolymers, graft polymers or random polymers.

[0039] The polymers may be opaque or translucent but preferably transparent. The polymers may be selected for example from the group of thermoplastic polymers like polyesters, poly amides, polyimides, polyamide-imides, polyamide esters, polyurethanes, polyureas, polyolefines; polymers from substituted olefines like vinyl ethers, vinyl esters, vinyl alcohols, vinyl chloride, vinylidichloride, acetonitrile, acrylic acid, methacrylic acid, esters and amides of acrylic acid and methacrylic acid, styrene, chlorostyrene, methylstyrene, styrene sulfonic acid and their esters and amides, vinylcarbazole, vinylpyridine, vinylpyrrolidone; polymaleic acid and esters and amides therefrom; polyethers (for example from bisphenol-A diglycidyl ether), polysulfones, polyketones, polyphenylsulfides, and polyacetals; and natural polymers and their derivatives like cellulose and its esters and ethers, and starch or derivatives of starch.

[0040] Examples of thermosetting resins and structurally crosslinked resins are polyepoxides, unsaturated polyesters, photocrosslinked resins for example from acrylic acid and/or methacrylic esters and/or amides from polyols and/or polyamines, melamine/formaldehyde resins, and phenol/formaldehyde resins; polymers from butadiene, isoprene and or chloroprene and copolymers with olefins, which may be crosslinked and of rubbery nature, including latices; as well as silicates obtainable through the known sol/gel process.

[0041] The polymeric compositions of the invention may contain further ingredients to enhance certain features such as electrical, physical and mechanical properties, and/or the processability, for example dispersing agents to achieve a uniform distribution of particles, lubricants, plasticizers, antistatica, solvents, molding agents, antioxidants, light stabilizers, fillers and reinforcing fillers like glass balls and glass fibers, silicates (e.g. mica, clay, wollastonite), metal and semiconductor metal oxides, metal carbonates, metal salts, metals and semiconductor metals, carbon black, as powder, or carbon fibers, whiskers, metal and semiconductor metal carbides, metal and semiconductor metal nitrides, dyes, pigments and others.

[0042] The weight ratio of (host chromophores plus guest chromophores):polymer matrix is dependent on the actual practical application, hence there are no well defined preferred ratios, other than the broad range 99:1 to 1:999. In certain applications where both color strength and fluorescence are required, then the preferred ratios of the chromophores to the polymer matrix are 20:80 to 99:1, preferably 50:50 to 99:1 and more preferably 80:20 to 99:1. In circumstances where fluorescence is desired but color strength is not required, then the preferred ratio of the chromophores to the polymer matrix are 20:80 to 1:999, more preferably 10:90 to 1:999 and more preferably 5:95 to 1:999.

[0043] The composition according to the invention can be prepared using known processes like co-sublimation, as described in JP-A-03 255 190, or new processes that utilize the solubility of the guest chromophores.

[0044] A further embodiment of the invention is a process for the preparation of the inventive, abovementioned composition, comprising a host chromophore and a guest chromophore and, if desired, a polymer matrix, wherein the absorption spectrum of the guest chromophore overlaps with the fluorescence emission spectrum of the host chromophore, characterized in

(a) selecting the host chromophore from the group consisting of benzo[4,5]imidazo[2,1-a]-isoindol-11-ones,

- (b) mixing the host chromophore and an effective amount of at least one guest chromophore, and optionally a polymer or polymerisable precursor, in the presence of a solvent, and
 c) then precipitating the host and guest chromophores, optionally in the presence the polymer of step (b), or (d) precipitating the host and guest chromophores during polymerization of the polymer precursor of step (b).

[0045] In the context of the invention mixing of the materials can be achieved through dissolution of the components in a common solvent and followed by the subsequent evaporation of the solvent; precipitation from a good solvent into a poor solvent (vigorous stirring can be applied); freeze-drying; and precipitation during polymerization of polymerizable monomers or oligomers, preferably under vigorous stirring.

[0046] Suitable inert solvents are for example protic-polar and aprotic solvents, which may be used alone or in an admixture of at least two solvents. Examples are: water, alcohols (methanol, ethanol, propanol, butanol), ethyleneglycolmonomethyl- or -monoethylether, ethers (dibutylether, tetrahydrofuran, dioxane, ethyleneglycol dimethylether, ethyleneglycoldiethylether, diethyleneglycoldiethylether, triethyleneglycoldimethylether), halogenated hydrocarbons (methylenechloride, chloroform, 1,2-dichloroethane, 1,1,1-trichloroethane, 1,1,2,2-tetrachloroethane), carboxylic esters and lactones (acetic acid ethylester, propionic acid methylester, benzoic acid ethylester, 2-methoxyethylacetate, γ -butyrolactone, δ -valerolactone, pivalolactone), carboxylic acid amides and lactames; N,N-dimethylformamide, N,N-diethylformamide, N,N-dimethylacetamide, tetramethylurea, hexamethylphosphorous acidtriamide, γ -butyrolactame, ϵ -caprolactame, N-methylpyrrolidone, N-acetylpyrrolidone, N-methylcaprolactame; sulfoxides (dimethylsulfoxide), sulfones (dimethylsulfone, diethylsulfone, trimethylenesulfone, tetramethylenesulfone), tertiary amines (N-methylpiperidine, N-methylmorpholine), aliphatic and aromatic hydrocarbons like petroleumether, pentane, hexane, cyclohexane, methylcyclohexane, benzene or substituted benzenes (chlorobenzol, o-dichlorobenzene, 1,2,4-trichlorobenzene, nitrobenzene, toluene, xylene) and nitriles (acetonitrile, propionitrile, benzenenitrile, phenylacetonitrile), ketones (acetone, methyl-isobutyl-ketone).

[0047] The coprecipitation may be carried out in by a number of methods. When the host and guest chromophores possess solubilities affording the desired weight range in the final composition, the precipitation may be completed by adding the solution to a non-solvent, filtering off then the precipitate and removing the solvent, preferably in drying the solid at elevated temperatures and preferably under vacuum. Another possibility is to simply evaporate the solvent under vacuum and/or elevated temperatures.

[0048] In the process of freeze-drying, a steady state of components and solvent in general is generated by freezing a solution, wherein the components are in homogeneous distribution. This state is maintained upon removal of the solvent by freeze-drying. The furnished materials are usually highly fluorescent and exhibit all the features characteristic of host/guest materials.

[0049] In another preferred embodiment the host and guest chromophores are dissolved in a suitable solvent, and then this solution is added to a polymer gel (polymer swollen with a solvent). Usually the host and guest chromophores are in turn soaked into the gel. As a rule, removal of the solvent and drying generates a composition according to the invention.

[0050] In another preferred embodiment host and guest chromophores are milled together using a ball mill. Due to the high shearing forces usually the guest chromophore particles and/or molecules penetrate into the host chromophore matrix, forming a fluorescent composition according to the invention.

[0051] In another preferred embodiment the host and guest chromophores are mixed, optionally together with a polymer, and then melt-mixed at temperatures below the respective decomposition temperatures of the individual components.

[0052] The compositions on hand can span a broad number of applications. For example, the inventive compositions could be rendered very useful as coloring agents in applications such as road markings and traffic signs for night and daylight uses, as they exhibit brilliant daylight fluorescence and can also be excited by the UV radiation of motor vehicles halogen lamps, thereby providing intense, bright colors during both day and nighttime. Other applications include their use as pigments, coloring agents, materials for scintillators, materials for solar energy collectors, materials for light emitting electroluminescent devices, materials for generating fluorescent images. Moreover, the choice of guest compound can lend a lot of flexibility to the desired emission wavelength required of the overall system, therein imparting the capability for color-tuning and ease of tailoring of the core system to specific color applications via wavelength modulation. It is also possible to produce fluorescent images (high relief structures) by the well known photoresist technology. The compositions of the invention may also be used in paints, lacquers and printing inks.

[0053] The compositions according to the invention may be used in various forms depending upon the end use purpose.

[0054] The compositions according to the invention may be milled to generate a powdery form for industrial applications.

[0055] Another embodiment of the invention is a composition according to the invention in form of a powder, which contains particles. The particles may have an average diameter from 10 nm to 500 μ m, more preferably 50 nm to 100

μm and most preferably 50 nm to 50 μm . The powders also include polymer particles containing the host and guest chromophores dissolved and uniformly distributed therein, and can be obtained via grinding or emulsion polymerization, or both.

[0056] The particles of the composition of the invention may be encapsulated with polymers by known methods to generate for example pigments for coloring polymers.

The compositions according to the invention may be used as a coating to form a layer on support materials, preferably via a process of co-sublimation. A further embodiment of the invention is a support material to which on at least partially is coated a layer of the composition according to the invention.

[0057] Suitable support (or carrier) materials may be selected from the group consisting of organic or inorganic materials like glass, ceramics, minerals, plastics, paper, wood, semiconductors, metals, metal oxides and semiconductor metal oxides, and metal or semiconductor metal nitrides or -carbides.

[0058] The thickness of the layer depends on the desired use and usually may be from 0.01 to 1000 μm , preferably 0.05 to 500 μm , and especially preferred 0.1 to 100 μm .

[0059] The coatings may be protected by covering coatings which preferably are transparent. Such coatings are well known, in particular photocrosslinked coatings are useful for this purpose, and are well known in the art.

[0060] The powders according to the invention may be admixed with polymers. A further embodiment of the invention is a composition comprising (a) a polymer substrate, and (b) particles of the composition according to the invention, homogeneously distributed therein.

[0061] The amount of the particles may be for example 0.0001 to 90 weight%, preferably 0.1 to 90 weight% and more preferably 1 to 50 weight% of the total composition.

[0062] The polymer substrate may be selected from thermoplastics, polymer blends, thermosettings and structurally crosslinked polymers. The polymers may be homopolymers, copolymers, blockpolymers, graft polymers or random polymers.

[0063] The polymers may be opaque or translucent but preferably transparent. The polymers may be selected for example from the group of thermoplastic polymers like polyesters, polyamides, polyimides, polyamide-imides, polyamide esters, polyurethanes, polyureas, polyolefines; polymers from substituted olefines like vinyl ethers, vinyl esters, vinyl alcohols, vinyl chloride, vinylidene chloride, acetonitrile, acrylic acid, methacrylic acid, esters and amides of acrylic acid and methacrylic acid, styrene, chlorostyrene, methylstyrene, styrene sulfonic acid and their esters and amides, vinylcarbazole, vinylpyridine, vinylpyrrolidone; polymaleic acid and esters and amides therefrom; polyethers (for example from bisphenol-A diglycidyl ether), polysulfones, polyketones, polyphenylsulfides, and polyacetals; and natural polymers and their derivatives like cellulose and its esters and ethers, and starch or derivatives of starch.

[0064] Examples of thermosetting resins and structurally crosslinked resins are polyepoxides, unsaturated polyesters, photocrosslinked resins for example from acrylic acid and/or methacrylic esters and/or amides from polyols and/or polyamines, melamine/formaldehyde resins, and phenol/formaldehyde resins; polymers from butadiene, isoprene and/or chloroprene and copolymers with olefins, which may be crosslinked and of rubbery nature; as well as silicates obtainable for example through the known sol/gel process.

[0065] The thermoplastic compositions are for example obtainable by known mixing methods like admixing solutions of polymers and removing the solvent, injection molding and extrusion molding. Thermosetting and structurally crosslinked compositions are obtainable by known methods like press molding, whereby the particles usually are dispersed prior to the polymerization of a precursor composition.

[0066] The polymeric compositions of the invention may contain further ingredients to enhance certain features such as electrical, physical and mechanical properties, and/or the processability, for example dispersing agents to achieve a uniform distribution of particles, lubricants, plasticizers, antistatics, solvents, molding agents, antioxidants, light stabilizers, fillers and reinforcing fillers like glass balls and glass fibers, silicates (e.g. mica, clay, wollastonite), metal and semiconductor metal oxides, metal carbonates, metal salts, metals and semiconductor metals, carbon black, as powder, or carbon fibers, whiskers, metal and semiconductor metal carbides, metal and semiconductor metal nitrides, dyes, pigments and others.

[0067] The polymer compositions of the invention may be used in the form of shaped articles.

[0068] The polymer composition or a polymerisable precursor composition with host/guest particles may contain a solvent to generate coating compositions. Suitable solvents are mentioned before.

In another aspect of the invention the polymer composition containing particles of the host/guest composition or particles from polymers and dissolved host/guest chromophores may be used as coatings on carrier materials, using the above mentioned composition.

[0069] Another embodiment of the invention is a composition comprising (a) a carrier material and (b) at least on one surface a coating of a composition comprising (a) a polymer substrate, and (b) particles of the composition, or particles from polymers and dissolved host/guest chromophores, or both according to the invention, homogeneously distributed therein.

[0070] In another aspect of the invention the composition containing a polymer and soluble host/guest chromophores

may be used as coatings on carrier materials, using a solution of said composition.

[0071] Another embodiment of the invention is a composition comprising (a) a carrier material and (b) at least on one surface a coating of a composition comprising (a) a polymer matrix, and (b) a polymer and soluble host/guest chromophores according to the invention, homogeneously distributed therein.

[0072] Suitable carrier materials may be selected from organic or inorganic materials like glass, ceramics, minerals, plastics, paper, wood, textiles, semiconductors, metals, metal oxides and semiconductor metal oxides, and metal or semiconductor metal-nitrides or -carbides.

[0073] The thickness of the coating depends on the desired use and may be from 0.01 to 1000 μm , preferably 0.05 to 500 μm , and especially preferred 0.1 to 100 μm .

[0074] The coatings may be protected by covering coatings which preferably are transparent. Such coatings are well known, in particular photocrosslinked coatings are useful for this purpose, and are well known in the art.

[0075] The coated materials are obtainable by known methods like painting, casting or spincoating, directly or with dispersion of the polymeric compositions.

[0076] It is also possible to use a polymerisable composition containing polymer forming monomers or oligomeric precursors, in particular crosslinkable olefinically unsaturated monomers are useful in generating such coatings. The polymerization may be induced thermally or by actinic radiation or both. It is often preferred to carry-out the polymerisations in the presence of a radical initiator species. The coating compositions are novel and a further embodiment of the invention.

[0077] A further embodiment of the invention is a solvent containing liquid composition, comprising

(1) a soluble polymer, and

(2) particles of the host and guest chromophore of a composition according to the invention, or dissolved therein host and guest chromophores according to the invention.

[0078] These compositions may contain a solvent, such as those mentioned before, and optionally surfactants and dispersing agents. The viscosity range of the composition depends on the desired application, and can be readily by choice of solvent quantity, polymers binder and fluorescent materials. To further achieve a desired viscosity thickening agents may additionally be used. Suitable solvents have been mentioned.

[0079] The preparation of this composition can be achieved by simply mixing the ingredients together using suitable mixing equipment. Dispersions are in general stable depending upon the viscosity. Aggregated particles may be re-distributed by stirring.

[0080] In a highly advantageous embodiment of preparing coatings polymerisable compositions can be used, wherein at least one surface of a carrier material is coated and subsequently polymerized by heat, radiation or both. Photopolymerizable mixtures can also be used to generate fluorescent images by known photoresist technology.

[0081] A further embodiment of the invention is a polymerisable composition comprising polymerisable monomers or prepolymers in admixture with a composition according to the invention in the form of a powder containing particles, or with host and guest chromophores according to the invention, preferably dissolved therein, or both.

[0082] The composition may be used to generate the polymers or polymer particles according to the invention as described before. Preferably the composition contains a solvent, when coatings or images are to be generated. The afore described embodiments also apply to this composition, inclusive of the preferred embodiments.

[0083] In a preferred embodiment the composition is based on polymerisable monomers and/or prepolymers containing a group selected from olefinically unsaturated groups, preferably from $-\text{CH}=\text{CH}_2$ and $-\text{C}(\text{CH}_3)=\text{CH}_2$, which can be thermally or photo-polymerized.

[0084] Photopolymerisable monomers and prepolymers are well known in the art and described for example in EP-A-0 654 711. Preferred photopolymerisable monomers and prepolymers are those based on the esters or amides of acrylic acid or methacrylic acid and alcohols, polyols, amines and polyamines.

[0085] Preferred ethylenically unsaturated photopolymerisable agents are selected from the group of acrylic or methacrylic acid esters of aliphatic, cycloaliphatic and cycloaliphatic-aliphatic alcohols and diols to tetrols, and amines and diamines to tetramines containing especially preferred 2 to 12, and particularly preferred 2 to 8 C-atoms. Some examples of these diols are alkylenediols like ethylenglycol, 1,2- or 1,3-propanediol, 1,2-, 1,3- and 1,4-butanediol, pentanediol, hexanediol, octanediol, decanediol, dodecanediol, cyclohexanediol, di(hydroxymethyl)-cyclohexane, polyoxy-alkylenediols from preferably C_2 - C_6 alkylenediols with preferably 2 to 100 alkylenediol units, more preferably 2 to 50 alkylenediol units, and most preferably 2 to 20 alkylenediol units, like for example polyethylenediols, polypolypropylenediols, polybutylenediols and polyethylene/polypropylenediols, further 1,1,1-trihydroxymethylethane or -propane, pentaerythritol and dipentaerythritol. Some examples for polyamines are ethylenediamine, 1,3- and 1,3-propanediamine, 1,2-, 1,3- and 1,4-butanediamine, 1,6-hexanediamine, diethylenetriamine, triethylenetetramine, cyclohexanediamine, (aminomethyl)cyclohexanamine, isophorondiamine and di(aminomethyl)cyclohexane. Examples of alcohols are linear or branched C_1 to C_{20} alkanols.

[0086] The photopolymerisable composition may be particularly suitable for generating coatings and images.

[0087] A further embodiment of the invention is a composition comprising a carrier material with a high relief image of a polymerized photoresist material, which contains a composition according to the invention in the form of a powder containing particles, or host and guest chromophores according to the invention, or both, if desired dissolved and/or homogeneously distributed therein.

[0088] A further embodiment of the invention is a process for the preparation of fluorescent high relief images on a carrier. Preferably, this involves irradiating under a mask or by laser writing, the above coated photopolymerisable composition (which preferably has been dried and removed of solvent) on the carrier, developing the irradiated composition and finally removing the non-irradiated parts.

[0089] Removal of the non-irradiated parts in general is mostly carried out by treatment with solvent.

[0090] All highly fluorescent materials described before can broadly be used in optical and electrooptical devices.


[0091] A further embodiment of the invention is a process for the creation of fluorescent radiation which requires the excitation either electrically or by UV or visible radiation, or both, of a fluorescent composition according to the invention.

[0092] Another embodiment of the invention is the use of the compositions according to the invention as fluorescent materials.

[0093] As described before benzo [4,5] imidazo [2,1-a] isoindol-11-one, 1,2,3,4-tetrachloro-benzo [4,5] imidazo [2,1-a] isoindol-11-one and some substituted derivatives are known in the art. From our investigations it was found that benzo [4,5] imidazo [2,1-a] isoindol-11-ones and 1,2,3,4-tetrachloro-benzo [4,5] imidazo [2,1-a] isoindol-11-ones show very high light stabilities, as measured by a time dependent exposure testing. Furthermore, it was found that the light stability of these compounds is reduced by substitution in the 7- and/or 8-positions.

In the case of 1,2,3,4-tetraphenyl-benzo [4,5] imidazo [2,1-a] isoindol-11-one, it exhibits a moderate light stability, which suffices for a number of applications. However it was found, that the solid state luminescence is maintained, the light stability is greatly improved, and the compounds have a desired solubility, when the benzo [4,5] imidazo [2,1-a] isoindol-11-one is substituted in the 1-, 2-, 3- and/or 4-positions and in the 7- and/or 8-positions with selected substituents.

[0094] An embodiment of the invention is a compound of the formula V,



(V).

wherein

at most three of R_{13} , R_{14} , R_{15} and R_{16} are H and at least one of R_{13} , R_{14} , R_{15} and R_{16} are a substituent selected from the group of C_1 to C_{18} alkyl, C_1 to C_{18} alkoxy, C_1 to C_{18} alkylthio, C_1 to C_{12} alkoxy-poly C_2 to C_6 oxyalkylene; unsubstituted or with F, Cl, Br, -CN, C_1 to C_{12} alkyl, C_1 to C_{12} alkoxy, C_1 to C_{12} alkylthio, or $-NR_{21}R_{22}$ substituted C_5 to C_8 cycloalkyl, C_5 to C_8 cycloalkoxy, C_5 to C_8 cycloalkylthio, C_5 to C_8 cycloalkyl- C_1 to C_4 alkyl, C_5 to C_8 cycloalkyl- C_1 to C_4 alkoxy, C_5 to C_8 cycloalkyl- C_1 to C_4 alkylthio, phenyl, phenyloxy, phenylthio, phenyl- C_1 to C_4 alkyl, phenyl- C_1 to C_4 alkoxy, phenyl- C_1 to C_4 alkylthio; or

R_{13} and R_{14} together, R_{15} and R_{16} together, or R_{13} and R_{14} together and R_{15} and R_{16} together, or R_{14} and R_{15} together are selected from the groups $-CH=CR_{24}-CR_{25}=CH-$,

$-N=CR_{24}-CR_{25}=CH-$, $-CH=CR_{24}-CR_{25}=N-$, $-CH=N-CR_{25}=CH-$, $-CH=CR_{24}-N=CH-$, $-N=CR_{24}-CR_{25}=N-$, $-N=CR_{24}-N=CH-$, $-CH=CH-O-$, $-CH=CH-S-$, $-CH=CH-NR_{23}-$;

R_{17} and R_{20} independently from one another are H or have the meaning of R_{18} ; one of R_{18} and R_{19} are H and the other of R_{18} and R_{19} or both are a substituent selected from the group of C_1 to C_{18} alkyl, C_1 to C_{18} alkoxy, C_1 to C_{18} alkylthio, C_1 to C_{12} alkoxy-poly C_2 to C_6 oxyalkylene; unsubstituted or with F, Cl, Br, -CN, C_1 to C_{12} alkyl, C_1 to C_{12} alkoxy, C_1 to C_{12} alkylthio, or $-NR_{21}R_{22}$ substituted C_5 to C_8 cycloalkyl, C_5 to C_8 cycloalkoxy, C_5 to C_8 cycloalkylthio, C_5 to C_8 cycloalkyl- C_1 to C_4 alkyl, C_5 to C_8 cycloalkyl- C_1 to C_4 alkoxy, C_5 to C_8 cycloalkyl- C_1 to C_4 alkylthio, phenyl, phenyloxy, phenylthio, phenyl- C_1 to C_4 alkyl, phenyl- C_1 to C_4 alkoxy, phenyl- C_1 to C_4 alkylthio, phenyl- C_2 to C_{12} alkylidene, phenyl- $C(O)-$, phenyl- $NR_{23}-C(O)-$, phenyl- $NR_{23}-S(O)_2-$, phenyl- $S(O)-$, phenyl- $S(O)_2-$, phenyl- CO_2- , phenyl- $S(O)-O-$, phenyl- SO_3- , phenyl- $NR_{23}-$, or phenyl- $CH=CH-$; or

R₁₇ and R₁₈ together, R₁₉ and R₂₀ together, or R₁₇ and R₁₈ together and R₁₉ and R₂₀ together, or R₁₈ and R₁₉ together are selected from the groups -CH=CR₂₄-CR₂₅=CH-, -N=CR₂₄-CR₂₅=CH-, -CH=CR₂₄-CR₂₅=N-, -CH=N-CR₂₅=CH-, -CH=CR₂₄-N=CH-, -N=CR₂₄-CR₂₅=N-, -N=CR₂₄-N=CH-, -CH=CH-O-, -CH=CH-S-, -CH=CH-NR₂₃-;

R₂₁ and R₂₂ are independently from one another are C₁ to C₂₀alkyl, phenyl, C₁ to C₁₂alkylphenyl, benzyl or C₁ to C₁₂alkylbenzyl, or R₂₁ and R₂₂ together mean tetramethylene, pentamethylene or -CH₂CH₂-O-CH₂CH₂-;

R₂₃ is H C₁ to C₄alkyl or benzyl; and

R₂₄ and R₂₅ are independently from one another H, C₁ to C₆alkyl, C₁ to C₆alkoxy, C₁ to C₆alkylthio, or F, Cl or Br.

[0095] In a preferred embodiment R₁₃ and R₁₄ are substituents, and most preferably R₁₃, R₁₄, R₁₅ and R₁₆ are substituents. In still another preferred embodiment, R₁₃ and R₁₄, R₁₅ and R₁₆, R₁₄ and R₁₅, or R₁₃ and R₁₄ and R₁₅ and R₁₆ each together mean -CH=CR₂₄-CR₂₅=CH-, -N=CR₂₄-CR₂₅=CH-, -CH=CR₂₄-CR₂₅=N-, -CH=N-CR₂₅=CH-, -CH=CR₂₄-N=CH-.

[0096] In an other preferred embodiment R₁₇ and R₂₀ mean H, and R₁₇ and R₁₉ or both are substituents. In still another preferred embodiment, R₁₇ and R₁₈, R₁₉ and R₂₀, R₁₈ and R₁₉, or R₁₇ and R₁₈ and R₁₉ and R₂₀ each together mean -CH=CR₂₄-CR₂₅=CH-, -N=CR₂₄-CR₂₅=CH-, -CH=CR₂₄-CR₂₅=N-, -CH=N-CR₂₅=CH-, -CH=CR₂₄-N=CH-.

[0097] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is alkyl, it maybe linear alkyl or branched alkyl, and contain preferably 1 to 12 and more preferably 1 to 6 carbon atoms. Examples for alkyl have been given before. Preferred alkyls are methyl, ethyl, n- or i-propyl, n-, i- and t-butyl, and the isomers of pentyl and hexyl.

[0098] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is alkoxy, it maybe linear alkoxy or branched alkoxy, and contain preferably 1 to 12 and more preferably 1 to 6 carbon atoms. Examples for alkoxy have been given before. Preferred alkoxyes are methoxy, ethoxy, n- or i-propoxy, n-, i- and t-buoxty, and the isomers of pentoxy and hexoxy.

[0099] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is alkylthio, it maybe linear alkylthio or branched alkylthio, and contain preferably 1 to 12 and more preferably 1 to 6 carbon atoms. Examples for alkylthio have been given before. Preferred alkylthio are methylthio, ethylthio, n- or i-propylthio, n-, i- and t-butylthio, and the isomers of pentylthio and hexylthio.

[0100] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is C₁ to C₁₂alkoxy-polyC₂ to C₆oxyalkylene, the alkoxy maybe linear alkoxy or branched alkoxy and contains preferably 1 to 6 and more preferably 1 to 4 carbon atoms and may be for example methoxy, ethoxy, propoxy and butoxy. The oxyalkylene group preferably contains 2 to 4 and more preferably 2 or 3 carbon atoms and may be ethylenoxy or 1,2-propylenoxy. The residue may contain 1 to 12, preferably 1 to 6, and more preferably 1 to 4 repeating oxyalkylene units.

[0101] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is cycloalkyl, it is preferably cyclopentyl or cyclohexyl.

[0102] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is cycloalkoxy it is preferably cyclopentoxo or cyclohexoxo.

[0103] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is cycloalkylthio it is preferably cyclopentylthio or cyclohexylthio.

[0104] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is cycloalkyl-alkyl, the alkyl is preferably ethyl and most preferably methyl, and the cycloalkyl is preferably cyclopentyl or cyclohexyl. Preferred examples are cyclopentylmethyl and cyclohexylmethyl.

[0105] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and is cycloalkyl-alkoxy, the alkoxy is preferably ethoxy and most preferably methoxy, and the cycloalkyl is preferably cyclopentyl or cyclohexyl. Preferred examples are cyclopentyl-methoxy and cyclohexylmethoxy.

[0106] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ is cycloalkyl-alkylthio, the alkylthio is preferably ethylthio and most preferably methylthio, and the cycloalkyl is preferably cyclopentyl or cyclohexyl. Preferred examples are cyclopentyl-methylthio and cyclohexylmethylthio.

[0107] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is phenylalkyl the alkyl group preferably contains 1 or 2 carbon atoms and mostly preferred is methyl. Especially preferred is benzyl.

[0108] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is phenylalkoxy, the alkoxy group preferably contains 1 or 2 carbon atoms and mostly preferred is methoxy. Especially preferred is benzyloxy.

[0109] In the context of the invention when one or more of R₁₃, R₁₄, R₁₅ and R₁₆ as well as R₁₇, R₁₈, R₁₉ and R₂₀ is phenylalkylthio, the alkylthio group preferably contains 1 or 2 carbon atoms and mostly preferred is methylthio. Especially preferred is benzylthio.

[0110] In the context of the invention when one or more of R₁₇, R₁₈, R₁₉ and R₂₀ is phenyl-C₂ to C₁₂-alkylidene, the alkylidene may be linear or branched and may contain 2 to 6 and preferably 2 to 4 carbon atoms. Some examples are

ethylidene, 1,1- or 2,2-propylidene, and 1,1- or 2,2-butyldiene.

[0111] Preferred substituents are F, Cl, C₁ to C₄alkyl, C₁ to C₄alkoxy, C₁ to C₄alkylthio, and -NR₂₁R₂₂, wherein R₂₁ and R₂₂ are independently from one another is C₁ to C₁₂alkyl, phenyl or benzyl.

[0112] In the context of the invention when R₂₁ and R₂₂ are alkyl it may be linear alkyl or branched alkyl and may contain 1 to 12 and preferably 1 to 6 carbon atoms.

[0113] In the context of the invention when R₂₁ and R₂₂ are alkylphenyl, the alkyl may be linear or branched and may contain 1 to 8 and preferably 1 to 6 carbon atoms.

[0114] In the context of the invention when R₂₁ and R₂₂ are alkylbenzyl, the alkyl may be linear or branched and may contain 1 to 8 and preferably 1 to 6 carbon atoms.


[0115] R₂₃ is preferably H, methyl or ethyl.

[0116] In the context of the invention when R₂₄ and R₂₅ are alkyl, alkoxy, alkylthio may be linear or branched and may contain 1 to 4 and preferably 1 or 2 carbon atoms.

[0117] In a preferred embodiment R₁₃, R₁₄, R₁₅ and R₁₆ are preferably C₁ to C₄alkyl, C₁ to C₄alkoxy, phenyl, or C₁ to C₄alkylphenyl. Mostly preferred R₁₃, R₁₄, R₁₅ and R₁₆ are all phenyl.

[0118] In still a further preferred embodiment R₁₇ and R₂₀ are H, and R₁₈ and R₁₉ or both are C₁ to C₁₈alkyl or C₁ to C₁₈alkoxy, or R₁₇ and R₁₈, R₁₉ and R₂₀, R₁₈ and R₁₉, or R₁₇ and R₁₈ and R₁₉ and R₂₀ each together mean -CH=CR₂₄-CR₂₅=CH-, wherein R₂₄ and R₂₅ mean independently from one another H, F, Cl, C₁ to C₈alkyl or C₁ to C₈alkoxy.

[0119] In an especially preferred embodiment the compounds of formula V correspond to formula VI,




(VI),

wherein

R₁₇ and R₂₀ are H, and R₁₈ and R₁₉ or both are C₁ to C₁₈alkyl or C₁ to C₁₈alkoxy, or R₁₈ and R₁₉ together mean -CH=CR₂₄-CR₂₅=CH-; or R₁₇ and R₁₈ together or R₁₉ and R₂₀ together, or R₁₇ and R₁₈ together and R₁₉ and R₂₀ together mean -CH=CR₂₄-CR₂₅=CH-, wherein R₂₄ and R₂₅ are independently from one another H, F, Cl, C₁ to C₈alkyl or C₁ to C₈alkoxy. The alkyl is preferably branched in the α- or α,α-position.

[0120] It was also found that 1,2,3,4-tetrachloro-benzo [4,5] imidazo [2,1-a] isoindol-11-ones with α-branched alkyl substituents possess a higher light stability than the methyl substituted compounds, and that acyl substituted 1,2,3,4-tetrachloro-benzo [4,5] imidazo [2,1-a] isoindol-11-ones have also a high light stability and a desired solubility. A further embodiment of the invention are compounds of the formula VIa,



(VIa),

wherein

X₁ is Cl or Br,

one of R'₁₈ and R'₁₉ or both are independently from one another -COOH, or α- or α,α-branched C₃ to C₂₀alkyl or R_a-C(O)-, wherein R_a means C₁ to C₂₀alkyl; or C₅ to C₈cycloalkyl, C₅ to C₈cycloalkyl-CH₂-, phenyl, benzyl, which are unsubstituted or substituted with halogen, C₁ to C₁₂alkyl or C₁ to C₁₂alkoxy, or


one of R'₁₈ and R'₁₉ is α- or α,α-branched C₃ to C₂₀alkyl or R_a-C(O)-, wherein R_a means C₁ to C₂₀alkyl; or C₅ to C₈cycloalkyl, C₅ to C₈cycloalkyl-CH₂-, phenyl, benzyl, which are unsubstituted or substituted with halogen, C₁ to C₁₂alkyl or C₁ to C₁₂alkoxy, and the other of R'₁₈ and R'₁₉ is linear C₁ to C₁₂alkyl.

[0121] The branched alkyl is preferably selected from 1-methyl or 1,1-dimethyl substituted alk-1-yl. The alkyl preferably contains 3 to 18, more preferably 3 to 12, and most preferably 3 to 8 carbon atoms. X₁ is preferably Cl.

[0122] R_a means preferably C₃ to C₁₂alkyl; or cyclopentyl, cyclohexyl, phenyl, benzyl, which are unsubstituted or substituted with F, Cl, Br, C₁ to C₆alkyl or C₁ to C₆alkoxy.

[0123] In the context of the invention the linear alkyl contains preferably 1 to 8, more preferably 1 to 6, and most preferably 1 to 4 carbon atoms.

[0124] Compounds of the formulae V, VI and VIa can be prepared in analogy to known methods, e.g. described in EP-A 456 609, wherein the preparation method is based on the following equation:



Usually the two isomers indicated above are obtained which can be separated, if desired, e.g. by column chromatography. In general, it is not necessary for the success of this invention to separate the two structural isomers.

[0125] Another preferred embodiment of the present invention relates to the use of the inventive compounds V, VI and VIa as organic emitting materials in and for the preparation of electroluminescence ("EL") devices. Those EL-devices are well known in the art and e.g. described in US 5,593,788, WO 94/15441, and the literature cited therein. For example one of the common EL devices comprises two extremely thin layers (< 1.0 μm in combined thickness) which separate the anode and the cathode. One layer specifically is chosen to inject and transport holes and the other specifically chosen to inject and transport electrons and also acting as the organic luminescent zone of the device. The extremely thin organic luminescent medium offers reduced resistance, permitting higher current densities for a given level of electrical biasing. Since light emission is directly related to current density through the organic luminescent medium, the thin layers coupled with increased charge injection and transport efficiencies have allowed acceptable light emission levels (e.g. brightness levels capable of being visually detected in ambient light) to be achieved with low voltages in ranges compatible with integrated circuit drivers, such as transporting layer also acting as the luminescent zone of the device.

[0126] In another preferred embodiment of this invention, the inventive host/guest compositions can be used as organic emitting material in a layer of an EL device as well as for the preparation of such an EL device. Such devices are known in principle e.g. from US 5,593,788 and the prior art cited therein, hence, no further details are necessary for a skilled person in the art.

[0127] Hence, electroluminescent devices comprising the inventive compounds or compositions are also part of this invention. The preparation of such devices is given in detail e.g. in the above cited US 5,593,788 or WO 94/15441.


[0128] The fluorescent composition of the present invention emits solid state fluorescence with a greatly enhanced emission intensity when compared to the solid-state emission intensity of a powder that contains host units but lacks any guest units, or a powder that contains guest units but lacks any host units.

[0129] The compositions on hand do show the following advantages compared to known compositions:

- a) a greatly enhanced and intense fluorescence emission is generated,
- b) an intense solid state fluorescence is imparted, wherein the emission wavelengths are in the visible region of the electromagnetic spectrum,
- c) the composition can be excited using wavelengths in both the UV and visible regions,
- d) very good photostabilities and outdoor durabilities can be achieved,
- e) a wide range of emission wavelengths can be achieved through selection of guest molecules (color tuning),
- f) a high thermal stability can be achieved,
- g) easy preparation for the materials i.e. co-precipitation of the dissolved components is possible.

[0130] The following examples demonstrate the invention.

The designation of the benzo [4,5] imidazo [2,1-a] isoindol-11-ones relies on the following formula:



A) Preparation of benzo [4,5] imidazo [2,1-a] isoindol-11-ones.

Example A1: 1,2,3,4-tetraphenyl-benzo [4,5] imidazo [2,1-a] isoindol-11-one-7(or 8, A'1)-carboxylic acid (A1).

[0131] A 300 ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 4.58 g (30.1 mmol) of 3,4-diaminobenzoic acid, 13.6 g (30.0 mmol) of 1,2,3,4-tetraphenylphthalic anhydride, and 100 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 5 hours. The slurry is cooled and the yellow solid is isolated by filtration. The solid is washed with water and then with methanol. 10.9 g of yellow solid is obtained (64%).

¹H-NMR (CDCl₃, TMS) : δ 8.43 (d, J=1.2 Hz, 1H, H_{A9} or H_{A'6}), 8.33 (d, J=0.9 Hz, 1H, H_{A9} or H_{A'6}), 8.05 (dd, J=1.5, 8.4 Hz, 1H, H_{A7} or H_{A'8}), 7.96 (dd, J=1.6, 8.5 Hz, 1H, H_{A7} or H_{A'8}), 7.72 (d, J=8.3 Hz, 1H, H_{A6} or H_{A'9}), 7.61 (d, J=8.5 Hz, 1H, H_{A6} or H_{A'9}), 7.30-7.24 (m, 8H), 7.18-7.15 (m, 2H), 6.92-6.89 (m, 6H) 6.81-6.76 (m, 4H).

Example A2: 1,2,3,4-tetraphenyl-7-(t-butyl)-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A2) and 1,2,3,4-tetraphenyl-8-(t-butyl)-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A'2).

[0132] A 100ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 0.99 g (6.01 mmol) of 4-(t-butyl)-o-phenylenediamine, 2.73 g (6.03 mmol) of 1,2,3,4-tetraphenylphthalic anhydride, and 15 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 3 hours. The slurry is cooled and the yellow solid is isolated by filtration. The solid is washed with water. 2.5 g of yellow solid is obtained (total 71%; 42% for A2 and 29% for A'2). Two isomers can be separated by column chromatography using CH₂Cl₂ as eluent.

A2 (7-position):

[0133] ¹H-NMR (CDCl₃, TMS): δ 7.60 (d, J=1.3 Hz, 1H, H₆), 7.58 (d, J=8.4 Hz, 1H, H₉), 7.30 (dd, J=8.5, 1.4 Hz, 1H, H₈), 7.30-7.16 (m, 10H), 6.87-6.83 (m, 6H), 6.81-6.76 (m, 4H), 1.29 (s, 9H).

¹³C-NMR(in CDCl₃): δ 160.3 (s, C=O), 156.1 (s, C_{4b}), 149.6 (dt, C_{5a}), 148.3 (m, C₇), 147.9 (t, C₃), 145.5 (t, C₂), 141.9 (t, C₄ or C₁), 138.4 (m), 138.1 (m), 137.7 (C₄ or C₁), 136.1 (m), 135.5 (m), 130.9, 130.8, 130.3, 130.1 (s), 129.8, 127.7, 127.5, 127.1, 127.0, 126.4, 126.3, 123.9 (dm, J₁=160 Hz, C₈), 118.7 (dd, J₁=160 Hz, C₆), 111.6 (d, J₁=170 Hz, C₉), 35.0 (CMe₃), 31.6 (CH₃).

A'2 (8-position):

[0134] ¹H-NMR (CDCl₃, TMS): δ 7.73 (d, J=1.6 Hz, 1H, H₉), 7.47 (d, J=8.6 Hz, 1H, H₆), 7.28-7.22 (m, 9H), 7.20-7.17 (m, 2H), 6.93-6.89 (m, 6H), 6.82-6.78 (m, 4H), 1.32 (s, 9H).

^{13}C -NMR (CDCl_3): δ 160.6 (s, C=O), 155.6 (s, C_2), 150.3 (m, C_8), 147.9 (t, C_3), 147.4 (ddd, C_{5a}), 145.4 (t, C_2), 141.9 (t), 138.4 (m), 138.0 (m), 137.6 (t), 136.0 (m), 135.6 (m), 130.9, 130.8, 130.4, 130.2 (s), 129.8, 127.7, 127.5, 127.4, 127.1, 127.0, 126.3, 126.2, 122.4 (dd, $J^1=160$ Hz, C_7), 121.1 (d, $J^1=160$ Hz, C_6), 109.3 (ddd, $J^1=160$ Hz, C_9), 35.2 (CMe_3), 31.5 (CH_3).

Example A3: 1,2,3,4-tetraphenyl-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A3).

[0135] A 500ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 8.34 g (73.3 mmol) of o-phenylenediamine (95%), 33.0 g (66.3 mmol) of 1,2,3,4-tetraphenylphthalic anhydride, and 200 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 11 hours. The slurry is cooled and the yellow solid is isolated by filtration. The solid is washed with water and then with methanol. 35.1 g of an yellow solid is obtained (92%).

^1H -NMR (CDCl_3 , TMS): δ 7.66 (d, $J=7.6$ Hz, 1H), 7.55 (d, $J=7.7$ Hz, 1H), 7.30-7.15 (m, 12H), 6.93-6.88 (m, 6H), 6.81-6.76 (m, 4H).

MS: 524 ($[\text{M}]^+$).

Example A4: 1,2,3,4-tetraphenyl-7(or 8)-nitro-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A4, A'4).

[0136] A 100ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 1.53 g (9.99 mmol) of 4-nitro-o-phenylenediamine, 4.53 g (10.0 mmol) of 1,2,3,4-tetraphenylphthalic anhydride, and 25 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 1.33 hours. The slurry is cooled and the yellow solid is isolated by filtration. The solid is washed with water and then with methanol. 6.1 g of a pale yellow solid is obtained.(100%).

^1H -NMR (CDCl_3 , TMS): δ 8.57 (d, $J=2.2$ Hz, 1H, H_{A9} or $\text{H}_{A'6}$), 8.48 (d, $J=2.1$ Hz, 1H, H_{A9} or $\text{H}_{A'6}$), 8.22 (dd, $J=2.1$, 8.8 Hz, 1H, H_{A7} or $\text{H}_{A'8}$), 8.13 (dd, 1H, H_{A7} or $\text{H}_{A'8}$), 7.75 (d, $J=8.8$ Hz, 1H, H_{A6} or $\text{H}_{A'9}$), 7.65 (d, $J=8.9$ Hz, 1H, H_{A6} or $\text{H}_{A'9}$), 7.32-7.23 (m, 8H), 7.18-7.15 (m, 2H), 6.95-6.90 (m, 6H), 6.81-6.76 (m, 4H).

MS: 569 ($[\text{M}]^+$).

Example A5: 1,2,3,4-tetraphenyl-7(or 8)-methyl-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A5, A'5).

[0137] A 100ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 1.30 g (10.64 mmol) of 4-methyl-o-phenylenediamine, 4.53 g (10.01 mmol) of 1,2,3,4-tetraphenylphthalic anhydride, and 25 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 5 hours. The slurry is cooled and the yellow solid is isolated by filtration. The solid is washed with water and MeOH. 4.16 g of a yellow solid is obtained (77%).

^1H -NMR (CDCl_3 , TMS): δ 7.52 (d, $J=8.1$ Hz, 1H, H_{A6} or $\text{H}_{A'9}$), 7.48 (br s, 1H, H_{A9} or $\text{H}_{A'6}$),

7.42 (d, $J=8.2$ Hz, 1H, H_{A6} or $\text{H}_{A'9}$), 7.36 (br s, 1H, H_{A9} or $\text{H}_{A'6}$), 7.27-7.23 (m, 8H), 7.18-7.15

(m, 2H), 7.06 (br d, 1H, H_{A7} or $\text{H}_{A'8}$), 6.99 (br d, 1H, H_{A7} or $\text{H}_{A'8}$), 6.92-6.88 (m, 6H), 6.80-6.75 (m, 4H).

MS: 538 ($[\text{M}]^+$), 537 ($[\text{M}-\text{H}]^+$).

Example A6: 1,2,3,4-tetraphenyl-7(or 8)-methoxy-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A6, A'5).

[0138] A 100ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 1.38 g (9.99 mmol) of 4-methoxy-o-phenylenediamine, 4.52 g (9.99 mmol) of 1,2,3,4-tetraphenylphthalic anhydride, and 20 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 7 hours. The slurry is cooled and the yellow solid is isolated by filtration. The solid is washed with water, followed by purification with column chromatography. 3.75 g of yellow solid is obtained (68%).

^1H -NMR (CDCl_3 , TMS): δ 7.52 (d, $J=8.6$ Hz, 1H, H_{A6} or $\text{H}_{A'9}$), 7.42 (d, $J=8.9$ Hz, 1H, H_{A6} or $\text{H}_{A'9}$), 7.27-7.23 (m, 8H), 7.20 (d, $J=2.6$ Hz, 1H, H_{A9} or $\text{H}_{A'6}$), 7.19-7.14 (m, 2H), 7.08 (d, $J=2.4$ Hz, 1H, H_{A9} or $\text{H}_{A'6}$), 6.92-6.88 (m, 6H), 6.85 (dd, 1H, $J=2.4$, 8.7 Hz, H_{A7} or $\text{H}_{A'8}$), 6.80-6.74 (m, 1H, H_{A7} or $\text{H}_{A'8}$ +4H).

MS: 554 ($[\text{M}]^+$).

Example A7: 1,2,3,4-tetraphenyl-6,7-8,9-dibenzo-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A7).

[0139] A 100ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 0.84 g (4.03 mmol) of 9,10-diaminophenanthrene, 1.83 g (4.04 mmol) of 1,2,3,4-tetraphenylphthalic anhydride, and 15 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 5 hours. The slurry is cooled and the orange solid is isolated by filtration. The solid is washed with water and MeOH, followed by purification with column chromatography. 2.01 g of an orange solid is obtained (80%).

¹H-NMR (CDCl₃, TMS): δ 9.19 (dd, J=1.5, 8.0 Hz, 1H, H₉ or H₁₀), 8.70 (dd, J=7.8 Hz, 1H, H₉ or H₁₀), 8.64 (m, 1H, H₆ or H₁₃), 8.32 (m, 1H, H₆ or H₁₃), 7.64-7.59 (m, 4H, H_{7,8,11,12}), 7.37-7.28 (m, 8H), 7.25-7.22 (m, 2H), 6.96-6.90 (m, 6H), 6.86-6.79 (m, 4H).

Example A8: 1,2,3,4-tetrachloro-7(or 8)-nitro-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A8, A'8).

[0140] A 200ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 2.30 g (15.0 mmol) of 4-nitro-o-phenylenediamine, 4.29 g (15.0 mmol) of 1,2,3,4-tetrachlorophthalic anhydride, and 60 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 2 hours. The slurry is cooled and the pale yellow solid is isolated by filtration. The solid is washed with water and MeOH. 5.48 g of a pale yellow solid is obtained (91%).

¹H-NMR (CDCl₃, TMS): δ 8.75 (dd, J=1.7 Hz, 1H, H_{A9} or H_{A'8}), 8.74 (dd, J=2.3 Hz, 1H, H_{A9} or H_{A'8}), 8.40 (dd, J=2.2, 8.8 Hz, 1H, H_{A7} or H_{A'8}), 8.32 (dd, J=2.3, 8.9 Hz, 1H, H_{A7} or H_{A'8}), 7.97 (dd, J=8.7 Hz, 1H, H_{A6} or H_{A'9}), 7.96 (dd, J=9.0 Hz, 1H, H_{A6} or H_{A'9}).

MS: 403 ([M+2]⁺), 401 ([M]⁺).

Example A9: 1,2,3,4-tetrachloro-benzo [4,5] imidazo [2,1-a] isoindol-11-one-7(or 8)-carboxylic acid (A9, A'9).

[0141] A 1l round-bottom flask equipped with a stirrer and reflux condenser is charged with 15.2 g (100 mmol) of 3,4-diaminobenzoic acid, 28.6 g (100 mmol) of tetrachlorophthalic anhydride, and 450 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 15 hours. The slurry is cooled and the greenish yellow solid is isolated by filtration. The solid is washed with water and methanol. 37.0 g of a greenish yellow solid is obtained (92%).

MS: 404 ([M+4]⁺), 402 ([M+2]⁺), 400 ([M]⁺), 387 ([M+4-OH]⁺), 385 ([M+2-OH]⁺), 383 ([M-OH]⁺).

Example A10: 1,2,3,4-tetrachloro-7(or 8)-(t-butyl)-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A10, A'10).

[0142] A 100ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 2.48 g (15.1 mmol) of 4-(2'-methyl-2'-propyl)-o-phenylenediamine, 4.30 g (15.0 mmol) of tetrachlorophthalic anhydride, and 40 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 3.5 hours. The slurry is cooled and the yellow solid is isolated by filtration. The solid is washed with water and methanol. 5.22 g of a yellow solid is obtained (84%).

¹H-NMR (CDCl₃, TMS): δ 7.82 (dd, J=0.5, 1.8 Hz, 1H, H_{A9} or H_{A'8}), 7.73 (dd, J=0.5, 8.6 Hz, 1H, H_{A6} or H_{A'9}), 7.42 (dd, J=1.8, 8.6 Hz, 1H, H_{A7} or H_{A'8}), 1.40 (s, 9H).

MS: 416 ([M+4]⁺), 414 ([M+2]⁺), 412 ([M]⁺), 401 ([M+4-CH₃]⁺), 399 ([M+2-CH₃]⁺), 397 ([M-cu₃]⁺).

Example A11: 1,2,3,4-tetrachloro-7(or 8)-benzoyl-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A11, A'11).

[0143] A 100ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 2.13 g (10.0 mmol) of 3,4-diaminobenzophenone, 2.87 g (10.0 mmol) of tetrachlorophthalic anhydride, and 23 ml of glacial acetic acid. Under nitrogen atmosphere, the mixture is stirred and heated at reflux for 3.5 hours. The slurry is cooled and the yellow solid is isolated by filtration. The solid is washed with water and methanol, followed by dissolving in hot CHCl₃ with a soxhlet extractor to remove insoluble impurities. After condensation, 3.36 g of a yellow solid is obtained (72%).

¹H-NMR (CDCl₃, TMS): δ 8.28 (dd, 1H, H_{A9} or H_{A'8}), 7.93 (dd, J=0.7, 8.5 Hz, 1H, H_{A6} or H_{A'9}), 7.87-7.82 (m, 3H, H_{A7} or H_{A'8}, and H_{2'}, 6'), 7.64 (tt, J=1.2, 7.5 Hz, 1H, H_{3',5'}), 7.52 (t, J=7.6 Hz, 2H, H₄).

MS: 464 ([M+4]⁺), 462 ([M+2]⁺), 460 ([M]⁺), 387 ([M+4-C₆H₅]⁺), 385 ([M+2-C₆H₅]⁺), 383 ([M-C₆H₅]⁺), 359 ([M+4-C₆H₅CO]⁺), 357 ([M+2-C₆H₅CO]⁺), 355 ([M-C₆H₅CO]⁺).

Example A12: 1,2,3,4-tetrachloro-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A12).

[0144] Compound A12 is prepared according to the procedure described in EP-A-0 456 609.

B) Preparation of guest chromophores

Example B1: N,N'-dibenzyl-quinacridone (B1).

[0145] A 500ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 3.13g (10.0 mmol) of quinacridone (hereinafter referred to QA), 17.11 g (100 mmol) of benzyl bromide, 138.21 g (1.00 mol) of K_2CO_3 and 200 ml of dimethylformamide (DMF). Under a nitrogen atmosphere, the mixture is stirred and heated at reflux for 7.5 hours. The slurry is cooled and the orange solid is isolated by filtration. The solid is washed with water, acetone and ethanol. There yields 4.34 g of an orange solid (88%).

1H -NMR (DMSO- d_6 , Dimethylsulfoxide(DMSO)) : δ 8.56 (s, 2H, H_1), 8.35 (dd, $J=7.9$ Hz, 2H, H_5), 7.79 (dt, $J=8.2$ Hz, 2H, H_4), 7.67(d, $J=8.6$ Hz, 2H, H_2), 7.37 (t, 4H, H_3), 7.33 (t, 2H, H_6), 7.31 (t, 2H, H_7), 7.27 (d, 4H, H_8), 5.29 (s, 4H, H_9).

Example B2: N,N'-dibenzyl-diphenyl-diketopyrrolopyrrol

[0146] A 100ml round-bottom flask equipped with a stirrer and reflux condenser is charged with 1.47 g (5.1 mmol) of diphenyl-diketopyrrolopyrrole (hereinafter referred to DPP), 3.44 g (20.1 mmol) of benzyl bromide, 1.38 g (10.0 mmol) of K_2CO_3 and 50 ml of DMF. Under nitrogen atmosphere, the mixture is stirred and heated at 100°C for 42.5 hours. The slurry is cooled and the orange solid is isolated by filtration. The solid is washed with water and MeOH, followed by dissolving in hot $CHCl_3$. This $CHCl_3$ solution is applied to silica gel column using CH_2Cl_2 as eluent. After condensation, 1.21 g of an orange solid is obtained (51%).

1H -NMR ($CDCl_3$, TMS): δ 7.75 (d, $J=7.1$ Hz, 4H, H_1), 7.49-7.43 (m, 6H, H_2 and H_3), 7.30 (t, $J=7.4$ Hz 4H H_5), 7.24 (t, $J=7.3$ Hz, 2H, H_6), 7.19 (d, $J=7.4$ Hz, 4H, H_4), 4.99 (s, 4H, H_7).

MS: 468 ($[M]^+$).

C) Preparation of fluorescent compositions

Example C1:

[0147] 1.0×10^{-4} mol (0.0557 g) of A1 as a host compound and various amounts of Rhodamine 19 (Kodak Laboratory Chemicals) as a guest compound (B3) or Rhodamine 6G (Kodak Laboratory Chemicals) as a guest compound (B4) are dissolved in 20 ml of 1,2-dichloroethane and mixed. The solvent is then evaporated using a rotary evaporator (RE47, Yamato Scientific Co., LTD.) to obtain fluorescent powders including A1 and B3 or B4 of various concentrations.

[0148] Photoluminescence spectra of the fluorescent powders are measured using a fluorescence spectrophotometer in standard reflection mode (F-4500, HITACHI Co., LTD.) with a solid sample holder by exciting the host compound at absorption band thereof with monochromatic light ($\lambda_{max}=360$ nm). The results are listed in Table 1.

Table 1:

Fluorescent properties of fluorescent powders				
Host	Guest	Guest concentration	Photoluminescence spectrum	
		(mol %)	Peak wavelength (nm)	Peak intensity
A1	none	0	512	545
A1	B3	0.1	571	987
A1	B3	0.2	573	1040
A1	B3	0.5	580	869
A1	B4	0.2	579	968

Example C2:

[0149] 1.0×10^{-4} mol (0.0557 g) of A1 and various amounts of B1 are dissolved in 20 ml of 1,2-dichloroethane and mixed. The solvent is then sublimed by freeze-drying with a freeze-dryer (FD81, Tokyo Rikakikai Co., LTD.) to obtain fluorescent powders including A1 and B1 of various concentrations. Photoluminescence spectra of the fluorescent powders are measured in the same manner as in Example C1. The results are listed in Table 2.

Table 2:

Fluorescent properties of fluorescent powders including A1 and B1				
Host	Guest	Guest concentration	Photoluminescence spectrum	
		(mol %)	Peak wavelength (nm)	Peak intensity
A1	none	0	510	570
A1	B1	0.1	563	687
A1	B1	0.2	565	1014
A1	B1	0.5	564	964

Example C3:

[0150] 3.0×10^{-4} mol (0.1706 g) of A2 or A'2 as a host compound and various amounts of B1 or B2 as a guest compound are dissolved in 20 ml of 1-methyl-2-pyrrolidone and mixed. The solution is then poured into 400 ml of water which is vigorously stirred with a homogenizer (ULTRA-TURRAX T25. IKA-Labortechnik). A precipitate is filtered and dried in vacuo at 60°C to obtain fluorescent powders including A2 or A3 and B1 or B2 of various concentrations. Photoluminescence spectra of the fluorescent powders are measured in the same manner as in Example C1. The results are listed in Tables 3 and 4.

Table 3.

Fluorescent properties of fluorescent powders including A2 and B1 or B2				
Host	Guest	Guest concentration	Photoluminescence spectrum	
		(mol %)	Peak wavelength (nm)	Peak intensity
A2	none	0	526	197
A2	B1	0.2	523	1155
A2	B1	0.5	524	2005
A2	B1	1.0	526	2555
A2	B1	2.0	528	2876
A2	B1	5.0	529	1579
A2	B2	1.0	534	2054
A2	B2	2.0	537	2324
A2	B2	5.0	542	2160

Table 4:

Fluorescent properties of fluorescent powders including A'2 and B1 of				
Host	Guest	Guest concentration	Photoluminescence spectrum	
		(mol %)	Peak wavelength (nm)	Peak intensity
A'2	none	0	522	552
A'2	B1	1.0	524	2854
A'2	B1	2.0	525	3942
A'2	B1	5.0	529	2227

Example C4:

[0151] Carefully measured amounts of A1 as a host compound, B1 as a guest compound and an acrylic polymer (PMMA; polymethylmethacrylate, Aldrich Chemical Co. Inc.) are dissolved in CHCl_3 /methanol (95/5 vol.%) (Wako Chemical Co. Ltd.), to yield a clear, homogeneous solution (5wt% concentration). The mixture is then cast onto a glass substrate using a wire bar (KCC rod No. 8, RK Print-Coat Instruments) and the solvent removed. At this point the polymer film has the visual color and spectroscopic features typical of the precursor. Photoluminescence spectra of the fluorescent films are measured in the same manner as in Example C1. The results are listed in Table 5.

Table 5:

Fluorescent properties of the polymer films				
A ₁	B1	PMMA	Photoluminescence spectrum	
(wt%)	(wt %)	(wt%)	Peak wavelength (nm)	Peak intensity
5	0	95	501	401
5	0.05	95	545	561
5	0.1	95	548	564
5	0.2	95	552	586
5	0.3	95	555	788
10	0	90	501	440
10	0.05	90	546	593
10	0.1	90	551	819
10	0.2	90	553	811
10	0.3	90	559	896
30	0	70	501	461
30	0.05	70	551	621
30	0.1	70	552	781
30	0.2	70	556	734
30	0.3	70	558	799

Example C5:

[0152] 0.1g of the fluorescent powder of Example C3, which includes A2 as host and B2 as guest, is dispersed in 1.0 g of a functional acrylate monomer [KAYARAD D310 (Nippon Kayaku Co.)] using a homogenizer (ULTRA-TURRAX T25. IKA-Labortechnik). 5.0g of a 10wt% of polyvinylalcohol (PVA-117, Kurare) aqueous solution is added over the period of about 10 minutes to the vigorously stirred dispersion to give an uniform suspension, and recrystallized $K_2S_2O_8$ as initiator is added at room temperature. The reaction mixture is removed of oxygen by bubbling with N_2 gas for approximately 30 minutes, then placed in a temperature controlled water bath at 80°C for 10 hours. Highly cross-linked polymer particles containing fluorescent powder are obtained and isolated by filtration. The particles are then washed oftentimes with water and methanol. Drying is performed in a vacuum oven at 60 °C overnight. Yield 34.4%. Photoluminescence spectra of the fluorescent polymer particles are measured in the same manner as described in Example C1. The results are listed in Table 6.

Table 6:

Fluorescent properties of fluorescent polymer powders.				
Host	Guest	Guest concentration	Photoluminescence spectrum	
		(mol %)	Peak wavelength (nm)	Peak intensity
A2	none	0	525	370
A2	B2	5.0	538	1520

[0153] Example C6: 0.1 g of A2 as host, none or 0.002g of B2 as guest and 1.0 g of a functional acrylate monomer (KAYARAD D310) are dissolved in 10 ml of 1-methyl-2-pyrrolidone. The solution is then poured dropwise into 200ml of 2wt% of polyvinylalcohol (PVA-117, Kurare) aqueous solution which is vigorously stirred with a homogenizer. A yellow precipitate with green fluorescence is immediately generated, to which the recrystallized initiator $K_2S_2O_8$ is added. The reaction mixture is removed of oxygen by bubbling through N_2 gas for approximately 30 minutes, and placed in a temperature controlled water bath at 80°C for 10 hours. Highly crosslinked polymer particles are obtained and isolated by filtration. The particles are then washed oftentimes with water and methanol. Drying is performed in a vacuum oven at 60 °C overnight. Yield 42.5%. Photoluminescence spectra of the fluorescent polymer particles are measured in the same manner as described in Example C1. The results are listed in Table 7.

Table 7:

Fluorescent properties of fluorescent polymer powders.				
Host	Guest	Guest concentration	Photoluminescence spectrum	
		(wt %)	Peak wavelength (nm)	Peak intensity
A2	none	0	524	410
A2	B2	2.0	531	1790

[0154] Example C7: To an all glass reaction flask fitted with a rubber seal, magnetic stirrer, and maintained under a nitrogen atmosphere, 30ml of degassed water is charged and heated to 60 °C. Maintaining the reaction temperature of 60 °C, a degassed slurry of 2.08g (20 wt%) A12, 5.12g (49 wt%) ethylene glycol dimethacrylate, 3.1g (30 wt%) methyl methacrylate, none or 0.103g (1 wt%) Lumogen F Orange (BASF), 0.16g 2,2'- Azobis(isobutyronitrile) and 10 ml chloroform are added in a single addition. The vigorously stirred reaction is allowed to proceed for 6 hours, and then the reaction mixture is filtered. The precipitate consists of bright orange particles, that are non-uniform in shape and size. These particles are washed with water several times and dried at the water aspirator. Final drying is performed in a vacuum oven at 60 °C overnight. Yield 90%. The polymer powder thus obtained is ground into a fine powder, via a standard laboratory mortar and pestle. Photoluminescence spectra of the fluorescent polymer powders are measured in the same manner as described in Example C1. The results are listed in Table 8.

Table 8:

Fluorescent properties of fluorescent polymer powders.				
Host	Guest	Guest concentration	Photoluminescence spectrum	
		(wt %)	Peak wavelength (nm)	Peak intensity
A12	none	0	511	242
A12	Lumogen F Orange	1.0	584	680

Example C8: Light stability of 1,2,3,4-tetraphenyl-benzo [4,5] imidazo [2,1-a] isoindol-11-ones.

[0155] 1,2,3,4-tetraphenyl-7(or 8)-methoxy-benzo [4,5] imidazo [2,1-a] isoindol-11-one and various derivatives are charged in the sample holder used in Example C1. The samples are exposed to light with a Xenon lamp weatherometer (WEL-15X-HC-B.Ec, Suga Test instruments Co.) for 100 hours under the following conditions:

light intensity: 0.35 W/cm² at 340 nm,
temperature: 63°C at black panel,
humidity: 50%.

[0156] The intensity of the photoluminescence is measured prior to light exposure and the intensity loss in percent is measured after 100 hours of light exposure as described in example C1, comparing the peak heights. The results are summarized in table 9.

Table 9:

Light stability of stability of 1,2,3,4-tetraphenyl-benzo [4,5] imidazo [2,1-a] isoindol-11-ones.				
Compound	λ_{\max} (nm)	Intensity prior to	Intensity after	Loss (%)
		exposure	exposure	
A3	505	1211	759	37
A2	517	810	751	7
A'2	505	2033	1595	22
A5	533	488	390	20
A6	556	45	45	<1
A7	598	159	152	4

Example C9: Light stability of 1,2,3,4-tetrachloro-7-methyl-benzo [4,5] imidazo [2,1-a] isoindol-11-one and other derivatives.

[0157] The procedure of example C8 is repeated but this time using 1,2,3,4-tetrachloro-7-methylbenzo [4,5] imidazo [2,1-a] isoindol-11-one (A") as comparison with 1,2,3,4-tetrachloro-7-t-butyl-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A10) and 1,2,3,4-tetrachloro-7-benzoyl-benzo [4,5] imidazo [2,1-a] isoindol-11-one (A11). The results are summarized in table 10.

Table 10:


Compound	$\lambda_{\max}(\text{nm})$	Intensity prior to exposure	Intensity after exposure	Loss (%)
A"	534	170	142	17
A10	546	156	136	11
A11	524	273	247	10

Claims

1. A composition comprising (a) an effective amount of a guest chromophore embedded in a matrix of a host chromophore, or (b) a host chromophore and an effective amount of a guest chromophore both embedded in a polymer matrix, wherein the absorption spectrum of the guest chromophore overlaps with the fluorescence emission spectrum of the host chromophore, wherein overlap means "spectral overlap" defined by the following integral

$$S = \int_0^{+\infty} f_F(v) f_A(v) dv$$


wherein $f_F(v)$ is normalized, so that $\int_0^{+\infty} f_F(v) dv$ is equal to fluorescence quantum yield of the host, and where v is the wave number, f_F the fluorescence spectrum of the host measured in quanta, and f_A the spectral distribution of the molar extinction coefficient of the guest; and wherein the host chromophore is selected from the group consisting of benzo [4,5] imidazo [2,1-a] isoindol-11-ones of formula



(V),

wherein at most three of R_{13} , R_{14} , R_{15} and R_{16} are H and at least one of R_{13} , R_{14} , R_{15} and R_{16} are a substituent selected from the group of C_1 to C_{18} alkyl, C_1 to C_{18} alkoxy, C_1 to C_{18} alkylthio, C_1 to C_{12} alkoxy-poly C_2 to C_6 oxyalkylene; unsubstituted or with F, Cl, Br, -CN, C_1 to C_{12} alkyl, C_1 to C_{12} alkoxy, C_1 to C_{12} alkylthio, or -NR₂₁R₂₂ substituted or selected from C_5 to C_8 acloalkyl, C_5 to C_8 cycloalkoxy, C_5 to C_8 cycloalkylthio, C_5 to C_8 cycloalkyl-C₁ to C_4 alkyl, C_5 to C_8 cycloalkyl-C₁ to C_4 alkoxy, C_5 to C_8 cycloalkyl-C₁ to C_4 alkylthio, phenyl, phenyloxy, phenylthio, phenyl-C₁ to C_4 alkyl, phenyl-C₁ to C_4 alkoxy, phenyl-C₁ to C_4 alkylthio; or R_{13} and R_{14} together, R_{15} and R_{16} together, or R_{13} and R_{14} together and R_{15} and R_{16} together, or R_{14} and R_{15} together are selected from the groups -CH=CR₂₄-CR₂₅=CH-, -N=CR₂₄-CR₂₅=CH-, -CH=CR₂₄-CR₂₅=N-, -CH=N-CR₂₅=CH-, -CH=CR₂₄-N=CH-, -N=CR₂₄-CR₂₅=N-, -N=CR₂₄-N=CH-, -CH=CH-O-, -CH=CH-S-, -CH=CH-NR₂₃-; R_{17} and R_{20} independently from one another are H or have the meaning of R_{18} ; one of R_{18} and R_{19} are H and the other of R_{18} and R_{19} or both are a substituent selected from the group of C_1 to C_{18} alkyl, C_1 to C_{18} alkoxy, C_1 to C_{18} alkylthio, C_1 to C_{12} alkoxy-poly C_2 to C_6 oxyalkylene; unsubstituted or with F, Cl, Br, -CN, C_1 to C_{12} alkyl, C_1 to C_{12} alkoxy, C_1 to C_{12} alkylthio, or -NR₂₁R₂₂ substituted C_5 to C_8 cycloalkyl, C_5 to C_8 cycloalkoxy, C_5 to C_8 cycloalkylthio, C_5 to C_8 cycloalkyl-C₁ to C_4 alkyl, C_5 to C_8 cycloalkyl-C₁ to C_4 alkoxy, C_5 to C_8 cycloalkyl-C₁ to C_4 alkylthio, phenyl, phenyloxy, phenylthio, phenyl-C₁ to C_4 alkyl, phenyl-C₁ to C_4 alkoxy, phenyl-C₁ to C_4 alkylthio, phenyl-C₂ to C_{12} alkylidene, phenyl-C(O)-, phenyl-NR₂₃-C(O)-, phenyl-NR₂₃-S(O)₂-, phenyl-S(O)-, phenyl-S(O)₂-, phenyl-CO₂-, phenyl-S(O)-O-, phe-

nyl-SO₃⁻, phenyl-NR₂₃⁻, or phenyl-CH=CH-; or R₁₇ and R₁₈ together, R₁₉ and R₂₀ together, or R₁₇ and R₁₈ together and R₁₉ and R₂₀ together, or R₁₈ and R₁₉ together are selected from the groups -CH=CR₂₄-CR₂₅=CH-, -N=CR₂₄-CR₂₅=CH-, -CH=CR₂₄-CR₂₅=N-, -CH=N-CR₂₅=CH-, -CH=CR₂₄-N=CH-, -N=CR₂₄-CR₂₅=N-, -N=CR₂₄-N=CH-, -CH=CH-O-, -CH=CH-S-, -CH=CH-NR₂₃⁻; R₂₁ and R₂₂ are independently from one another are C₁ to C₂₀alkyl, phenyl, C₁ to C₁₂alkyl/phenyl, benzyl or C₁ to C₁₂alkyl/benzyl, or R₂₁ and R₂₂ together mean tetramethylene, pentamethylene or -CH₂CH₂-O-CH₂CH₂-; R₂₃ is H, C₁ to C₄alkyl or benzyl; and R₂₄ and R₂₅ are independently from one another H, C₁ to C₆alkyl, C₁ to C₆alkoxy, C₁ to C₆alkylthio, or F, Cl or Br, or of formula



(VIa),

wherein

X₁ is Cl or Br,

one of R'₁₈ and R'₁₉ or both are independently from one another -COOH, or α- or α,α-branched C₃ to C₂₀alkyl or R_a-C(O)-, wherein R_a means C₁ to C₂₀alkyl; or C₅ to C₈cycloalkyl, C₅ to C₈cycloalkyl-CH₂-, phenyl, benzyl, which are unsubstituted or substituted with halogen, C₁ to C₁₂alkyl or C₁ to C₁₂alkoxy, or

one of R'₁₈ and R'₁₉ is α- or α,α-branched C₃ to C₂₀alkyl or R_a-C(O)-, wherein R_a means C₁ to C₂₀alkyl; or C₅ to C₈cycloalkyl, C₅ to C₈cycloalkyl-CH₂-, phenyl, benzyl, which are unsubstituted or substituted with halogen, C₁ to C₁₂alkyl or C₁ to C₁₂alkoxy, and the other of R'₁₈ and R'₁₉ is linear C₁ to C₁₂alkyl, wherein the guest chromophore is luminescent in the molecular state and is selected from the group consisting of Quinacridones, perylenes, perinones, diketone- and dithioketopyrrolopyrroles, rhodamines, coumarins, xanthenes, oxazines, oxazoles, cyanines, phthalocyanines, porphyrines, styryl dyes, metal complexes and mixtures thereof.

2. A composition according to claim 1, **characterized in that** (a) the guest chromophore is homogeneously distributed within the matrix of the host chromophore, or (b) the host chromophore and the guest chromophore both are homogeneously distributed within the polymer matrix.

3. A process for the preparation of a composition according to claims 1 or 2, comprising a host chromophore and a guest chromophore and, if desired, a polymer matrix, wherein the absorption spectrum of the guest chromophore overlaps with the fluorescence emission spectrum of the host chromophore, **characterized in**

(a) selecting the host chromophore from the group consisting of benzo[4,5]imidazo[2,1-a]isoindol-11-ones of formula V or VIa,

(b) mixing the host chromophore and an effective amount of at least one guest chromophore, and optionally a polymer or polymerisable precursor, in the presence of a solvent, and

(c) then precipitating the host and guest chromophores, optionally in the presence the polymer of step (b), or

(d) precipitating the host and guest chromophores during polymerization of the polymer precursor of step (b).

4. A polymerisable composition comprising polymerisable monomers or prepolymers in admixture with a composition of claim 1 in the form of a powder containing particles, or with host and guest chromophores according to claim 1, preferably dissolved therein, or both.


5. A composition comprising a carrier material with a high relief image of a polymerized photoresist material, which contains a composition of claim 1 in the form of a powder containing particles, or host and guest chromophores according to claim 1, or both, if desired dissolved and/or homogeneously distributed therein.

6. A process for the preparation of fluorescent high relief images on a carrier, **characterized in** irradiating under a mask or by laser writing, the coated photopolymerisable composition according to claim 4, preferably dried and removed of solvent, on the carrier, developing the irradiated composition and finally removing the non-irradiated

parts.

7. Use of the compositions according to claims 1 or 2 or manufactured according to claim 3 as fluorescent materials.

8. A compound of the formula V,



(V),

wherein

at most three of R_{13} , R_{14} , R_{15} and R_{16} are H and at least one of R_{13} , R_{14} , R_{15} and R_{16} are a substituent selected from the group of C_1 to C_{18} alkyl, C_1 to C_{18} alkoxy, C_1 to C_{18} alkylthio, C_1 to C_{12} alkoxy-poly C_2 to C_6 oxyalkylene; unsubstituted or with F, Cl, Br, -CN, C_1 to C_{12} alkyl, C_1 to C_{12} alkoxy, C_1 to C_{12} alkylthio, or -NR₂₁R₂₂ substituted C_5 to C_8 cycloalkyl, C_5 to C_8 cycloalkoxy, C_5 to C_8 cycloalkylthio, C_5 to C_8 cycloalkyl- C_1 to C_4 alkyl, C_5 to C_8 cycloalkyl- C_1 to C_4 alkoxy, C_5 to C_8 cycloalkyl- C_1 to C_4 alkylthio, phenyl, phenyloxy, phenylthio, phenyl- C_1 to C_4 alkyl, phenyl- C_1 to C_4 alkoxy, phenyl- C_1 to C_4 alkylthio; or

R_{13} and R_{14} together, R_{15} and R_{16} together, or R_{13} and R_{14} together and R_{15} and R_{16} together are selected from the groups -CH=CR₂₄-CR₂₅=CH-,

-N=CR₂₄-CR₂₅=CH-, -CH=CR₂₄-CR₂₅=N-, -CH=N-CR₂₅=CH-, -CH=CR₂₄-N=CH-, -N=CR₂₄-CR₂₅=N-, -N=CR₂₄-N=CH-, -CH=CH-O-, -CH=CH-S-, -CH=CH-NR₂₃-;

R_{17} and R_{20} independently from one another are H or have the meaning of R_{18} ; one of R_{18} and R_{19} are H and the other of R_{18} and R_{19} or both are a substituent selected from the group of C_1 to C_{18} alkyl, C_1 to C_{18} alkoxy, C_1 to C_{18} alkylthio, C_1 to C_{12} alkoxy-poly C_2 to C_6 oxyalkylene; unsubstituted or with F, Cl, Br, -CN, C_1 to C_{12} alkyl, C_1 to C_{12} alkoxy, C_1 to C_{12} alkylthio, or -NR₂₁R₂₂ substituted C_5 to C_8 cycloalkyl, C_5 to C_8 cycloalkoxy, C_5 to C_8 cycloalkylthio, C_5 to C_8 cycloalkyl- C_1 to C_4 alkyl, C_5 to C_8 cycloalkyl- C_1 to C_4 alkoxy, C_5 to C_8 cycloalkyl- C_1 to C_4 alkylthio, phenyl, phenyloxy, phenylthio, phenyl- C_1 to C_4 alkyl, phenyl- C_1 to C_4 alkoxy, phenyl- C_1 to C_4 alkylthio, phenyl- C_2 to C_{12} alkylidene, phenyl-C(O)-, phenyl-NR₂₃-C(O)-, phenyl-NR₂₃-S(O)₂-, phenyl-S(O)-, phenyl-S(O)₂-, phenyl-CO₂-, phenyl-S(O)-O-, phenyl-SO₃-, phenyl-NR₂₃-, or phenyl-CH=CH-; or


R_{17} and R_{18} together, R_{19} and R_{20} together, or R_{17} and R_{18} together and R_{19} and R_{20} together are selected from the groups -CH=CR₂₄-CR₂₅=CH-, -N=CR₂₄-CR₂₅=CH-, -CH=CR₂₄-CR₂₅=N-, -CH=N-CR₂₅=CH-, -CH=CR₂₄-N=CH-, -N=CR₂₄-CR₂₅=N-, -N=CR₂₄-N=CH-, -CH=CH-O-, -CH=CH-S-, -CH=CH-NR₂₃-;

R_{21} and R_{22} are independently from one another are C_1 to C_{20} alkyl, phenyl, C_1 to C_{12} alkylphenyl, benzyl or C_1 to C_{12} alkylbenzyl, or R_{21} and R_{22} together mean tetramethylene, pentamethylene or -CH₂CH₂-O-CH₂CH₂-;

R_{23} is H C_1 to C_4 alkyl or benzyl; and

R_{24} and R_{25} are independently from one another H, C_1 to C_6 alkyl, C_1 to C_6 alkoxy, C_1 to C_6 alkylthio, or F, Cl or Br.

9. A compound according to claim 8, characterized in that it corresponds to formula VI,




(VI),

wherein

R_{17} and R_{20} are H, and R_{18} and R_{19} or both are C_1 to C_{18} alkyl or C_1 to C_{18} alkoxy, or R_{18} and R_{19} together mean $-CH=CR_{24}-CR_{25}=CH-$; or R_{17} and R_{18} together or R_{19} and R_{20} together, or R_{17} and R_{18} together and R_{19} and R_{20} together mean $-CH=CR_{24}-CR_{25}=CH-$, wherein R_{24} and R_{25} are independently from one another H, F, Cl, C_1 to C_8 alkyl or C_1 to C_8 alkoxy.

10. A compound of the formula VIa,



(VIa),

wherein

X_1 is Cl or Br,

one of R'_{18} and R'_{19} or both are independently from one another $-COOH$, or α - or α,α -branched C_3 to C_{20} alkyl or $R_a-C(O)-$, wherein R_a means C_1 to C_{20} alkyl; or C_5 to C_8 cycloalkyl, C_5 to C_8 cycloalkyl- CH_2- , phenyl, benzyl, which are unsubstituted or substituted with halogen, C_1 to C_{12} alkyl or C_1 to C_{12} alkoxy, or

one of R'_{18} and R'_{19} is α - or α,α -branched C_3 to C_{20} alkyl or $R_a-C(O)-$, wherein R_a means C_1 to C_{20} alkyl; or C_5 to C_8 cycloalkyl, C_5 to C_8 cycloalkyl- CH_2- , phenyl, benzyl, which are unsubstituted or substituted with halogen, C_1 to C_{12} alkyl or C_1 to C_{12} alkoxy, and the other of R'_{18} and R'_{19} is linear C_1 to C_{12} alkyl.

11. Use of the compounds V, VI and VIa according to claims 8 to 10 and the compositions according to claims 1 or 2 as organic emitting materials in and for the preparation of electroluminescence ("EL") devices.


12. Electroluminescence device comprising the compounds V, VI and VIa according to claims 8 to 10 or the compositions according to claims 1 or 2 as organic emitting materials.

Patentansprüche

1. Zusammensetzung, umfassend (a) eine wirksame Menge eines Gast-Chromophors der in eine Matrix eines Wirts-Chromophors eingebettet ist, oder (b) eines Wirts-Chromophors und einer wirksamen Menge eines Gast-Chromophors, die beide in einer Polymermatrix eingebettet sind, worin das Absorptionsspektrum des Gast-Chromophors mit dem Fluoreszenz-Emissionsspektrum des Wirts-Chromophors überlappt, worin Überlappen "spektrales Überlappen" bedeutet, das definiert ist durch das folgende Integral

$$S = \int_0^{+\infty} f_F(v) f_A(v) dv$$

worin $f_F(v)$ derart normalisiert ist, dass $\int_0^{+\infty} f_F(v) dv$ der Fluoreszenz-Quantenausbeute des Wirts entspricht und worin v die Wellenzahl ist, f_F das in Quanten gemessene Fluoreszenzspektrum des Wirts bedeutet und f_A die spektrale Verteilung des molaren Extinktionskoeffizienten des Gasts ist; und worin der Wirts-Chromophor ausgewählt ist aus der Gruppe, bestehend aus Benzo-[4,5]-imidazo-[2,1-a]-isoindol-11-onen der Formel



(V)

worin höchstens drei von R_{13} , R_{14} , R_{15} und R_{16} für H stehen und zumindest eines von R_{13} , R_{14} , R_{15} und R_{16} ein Substituent sind, ausgewählt aus der Gruppe von C_1 - bis C_{18} -Alkyl, C_1 - bis C_{18} -Alkoxy, C_1 - bis C_{18} -Alkylthio, C_1 - bis C_{12} -Alkoxy, C_1 - bis C_{12} -Alkylthio, oder $-NR_{21}R_{22}$ substituiertem, oder ausgewählt unter C_5 - bis C_8 -Cycloalkyl, C_5 - bis C_8 -Cycloalkoxy, C_5 - bis C_8 -Cycloalkylthio, C_5 - bis C_8 -Cycloalkyl- C_1 - bis C_4 -alkyl, C_5 - bis C_8 -Cycloalkyl- C_1 - bis C_4 -alkoxy, C_5 - bis C_8 -Cycloalkyl- C_1 - bis C_4 -alkylthio, Phenyl, Phenylthio, Phenyl- C_1 - bis C_4 -alkyl, Phenyl- C_1 - bis C_4 -alkoxy, Phenyl- C_1 - bis C_4 -alkylthio; oder

R_{13} und R_{14} gemeinsam, R_{15} und R_{16} gemeinsam, oder R_{13} und R_{14} gemeinsam und R_{15} und R_{16} gemeinsam, oder R_{14} und R_{15} gemeinsam ausgewählt sind aus den Gruppen $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{CH}=\text{N}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{N}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{CH}=\text{CH}-\text{O}-$, $-\text{CH}=\text{CH}-\text{S}-$, $-\text{CH}=\text{CH}-\text{NR}_{23}-$;


R_{17} und R_{20} unabhängig voneinander für H stehen oder die Bedeutung von R_{18} haben; eines von R_{18} und R_{19} für H steht und das andere von R_{18} und R_{19} oder beide ein Substituent sind, ausgewählt unter C_1 - bis C_{18} -Alkyl, C_1 - bis C_{18} -Alkoxy, C_1 - bis C_{18} -Alkylthio, C_1 - bis C_{12} -Alkoxy, C_1 - bis C_{12} -Alkylthio, oder $-NR_{21}R_{22}$ substituiertem C_5 - bis C_8 -Cycloalkyl, C_5 - bis C_8 -Cycloalkoxy, C_5 - bis C_8 -Cycloalkylthio, C_5 - bis C_8 -Cycloalkyl- C_1 - bis C_4 -alkyl, C_5 - bis C_8 -Cycloalkyl- C_1 - bis C_4 -alkoxy, C_5 - bis C_8 -Cycloalkyl- C_1 - bis C_4 -alkylthio, Phenyl, Phenylthio, Phenyl- C_1 - bis C_4 -alkyl, Phenyl- C_1 - bis C_4 -alkoxy, Phenyl- C_1 - bis C_4 -alkylthio, Phenyl- C_2 - bis C_{12} -alkylen, Phenyl- $C(O)-$, Phenyl- $\text{NR}_{23}-\text{C(O)}-$, Phenyl- $\text{NR}_{23}-\text{S(O)}_2-$, Phenyl- S(O)_2- , Phenyl- S(O)_2- , Phenyl- CO_2- , Phenyl- $\text{S(O)}_2-\text{O}-$, Phenyl- SO_3- , Phenyl- $\text{NR}_{23}-$ oder Phenyl- $\text{CH}=\text{CH}-$; oder

R_{17} und R_{18} gemeinsam, R_{19} und R_{20} gemeinsam, oder R_{17} und R_{18} gemeinsam und R_{19} und R_{20} gemeinsam, oder R_{18} und R_{19} gemeinsam ausgewählt sind unter den Gruppen $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{CH}=\text{N}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{N}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{CH}=\text{CH}-\text{O}-$, $-\text{CH}=\text{CH}-\text{S}-$, $-\text{CH}=\text{CH}-\text{NR}_{23}-$;

R_{21} und R_{22} unabhängig voneinander C_1 - bis C_{20} -Alkyl, Phenyl, C_1 - bis C_{12} -Alkylphenyl, Benzyl oder C_1 - bis C_{12} -Alkylbenzyl bedeuten, oder R_{21} und R_{22} gemeinsam Tetramethylen, Pentamethylen oder $-\text{CH}_2\text{CH}_2-\text{O}-\text{CH}_2\text{CH}_2-$ bedeuten;

R_{23} für H, C_1 - bis C_4 -Alkyl oder Benzyl steht; und

R_{24} und R_{25} unabhängig voneinander H, C_1 - bis C_6 -Alkyl, C_1 - bis C_6 -Alkoxy, C_1 - bis C_6 -Alkylthio, oder F, Cl oder Br bedeuten, oder der Formel



(VIa)

worin

X_1 für Cl oder Br steht,

eines von R'_{18} und R'_{19} oder beide unabhängig voneinander $-\text{COOH}$, oder α - oder α, α -verzweigtes C_3 - bis C_{20} -Alkyl oder $R_a-\text{C(O)}-$, worin R_a C_1 - bis C_{20} -Alkyl bedeutet; oder C_5 - bis C_8 -Cycloalkyl, C_5 - bis C_8 -Cycloalkyl- CH_2- , Phenyl, Benzyl, die unsubstituiert oder substituiert sind mit Halogen, C_1 - bis C_{12} -Alkyl oder C_1 - bis C_{12} -Alkoxy, bedeutet, oder eines von R'_{18} und R'_{19} ein α - oder α, α -verzweigtes C_3 - bis C_{20} -Alkyl oder $R_a-\text{C(O)}-$ bedeutet,

worin R_a C_1 - bis C_{20} -Alkyl bedeutet; oder C_5 - bis C_8 -Cycloalkyl, C_5 - bis C_8 -Cycloalkyl- CH_2 -, Phenyl, Benzyl, die unsubstituiert oder substituiert sind mit Halogen, C_1 bis C_{12} -Alkyl oder C_1 - bis C_{12} -Alkoxy bedeutet, und das andere von R'_{18} und R'_{19} lineares C_1 - bis C_{12} -Alkyl ist, worin der Gast-Chromophor in dem Molekularzustand lumineszent ist und ausgewählt ist aus der Gruppe, bestehend aus Chinacridonen, Perylenen, Perinonen, Diketo- und Dithio-ketopyrrolopyrrolen, Rhodaminen, Cumarinen, Xanthenen, Oxazinen, Oxazolen, Cyaninen, Phthalocyaninen, Porphyrinen, Styrylfarbstoffen, Metallkomplexen und Mischungen hiervon.

2. Zusammensetzung gemäß Anspruch 1, **dadurch gekennzeichnet, dass** (a) der Gast-Chromophor homogen innerhalb der Matrix des Wirts-Chromophors verteilt ist, oder (b) der Wirts-Chromophor und der Gast-Chromophor beide homogen innerhalb der Polymermatrix verteilt sind.

3. Verfahren zur Herstellung einer Zusammensetzung gemäß den Ansprüchen 1 oder 2, umfassend einen Wirts-Chromophor und einen Gast-Chromophor und gewünschtenfalls eine Polymermatrix, worin das Absorptionsspektrum des Gast-Chromophors mit dem Fluoreszenz-Emissionsspektrum des Wirts-Chromophors überlappt, **gekennzeichnet durch**

(a) Auswählen des Wirts-Chromophors aus der Gruppe, bestehend aus Benzo-[4,5]-imidazo-[2,1-a]-isoidol-11-onen der Formel V oder VIa,

(b) Mischen des Wirts-Chromophors und einer wirksamen Menge zumindest eines Gast-Chromophors und gegebenenfalls eines Polymeren oder polymerisierbaren Vorläufers, in Gegenwart eines Lösungsmittels, und

(c) hiernach Ausfällen der Wirts- und Gast-Chromophore, gegebenenfalls in Anwesenheit des Polymeren von Stufe (b), oder (d) Ausfällen der Wirts- und Gast-Chromophore während der Polymerisation des Polymer-Vorläufers von Stufe (b).


4. Polymerisierbare Zusammensetzung, umfassend polymerisierbare Monomere oder Prepolymere in Mischung mit einer Zusammensetzung von Anspruch 1 in Form eines Teilchen enthaltenden Pulvers, oder mit Wirts- und Gast-Chromophoren gemäß Anspruch 1, vorzugsweise hierin gelöst, oder beide.

5. Zusammensetzung, umfassend ein Trägermaterial mit einem Hochrelief-Bild eines polymerisierten Photoresistmaterials, das eine Zusammensetzung gemäß Anspruch 1 in Form eines Teilchen enthaltenden Pulvers oder Wirts- und Gast-Chromophore gemäß Anspruch 1 oder beide, wenn gewünscht hierin gelöst und/oder homogen verteilt, enthält.

6. Verfahren zur Herstellung von fluoreszierenden Hochrelief-Bildern auf einem Träger, **gekennzeichnet durch** Bestrahlen unter einer Maske oder **durch** Laser-Beschriften der aufgetragenen photopolymerisierbaren Zusammensetzung gemäß Anspruch 4, vorzugsweise getrocknet und von Lösungsmittel befreit, auf dem Träger, Entwickeln der bestrahlten Zusammensetzung und schließlich Entfernen der nicht-bestrahlten Teile.

7. Verwendung der Zusammensetzungen gemäß Anspruch 1 oder 2 oder hergestellt gemäß Anspruch 3 als fluoreszierende Materialien.

8. Verbindung der Formel V



worin höchstens drei von R_{13} , R_{14} , R_{15} und R_{16} für H stehen und zumindest eines von R_{13} , R_{14} , R_{15} und R_{16} ein Substituent sind, ausgewählt aus der Gruppe von C_1 - bis C_{18} -Alkyl, C_1 - bis C_{18} -Alkoxy, C_1 - bis C_{18} -Alkylthio, C_1 -

bis C₁₂-Alkoxy-poly-C₂- bis C₆-oxyalkylen; unsubstituiertem oder mit F, Cl, Br, -CN, C₁- bis C₁₂-Alkyl, C₁- bis C₁₂-Alkoxy, C₁- bis C₁₂-Alkylthio, oder -NR₂₁R₂₂ substituiertem C₅- bis C₈-Cycloalkyl, C₅- bis C₈-Cycloalkoxy, C₅- bis C₈-Cycloalkylthio, C₅- bis C₈-Cycloalkyl-C₁- bis C₄-alkyl, C₅- bis C₈-Cycloalkyl-C₁- bis C₄-alkoxy, C₅- bis C₈-Cycloalkyl-C₁- bis C₄-alkylthio, Phenyl, Phenylthio, Phenyl-C₁- bis C₄-alkyl, Phenyl-C₁- bis C₄-alkoxy, Phenyl-C₁- bis C₄-alkylthio; oder

R₁₃ und R₁₄ gemeinsam, R₁₅ und R₁₆ gemeinsam, oder R₁₃ und R₁₄ gemeinsam und R₁₅ und R₁₆ gemeinsam, oder R₁₄ und R₁₅ gemeinsam ausgewählt sind aus den Gruppen -CH=CR₂₄-CR₂₅=CH-, -N=CR₂₄-CR₂₅=CH-, -CH=CR₂₄-CR₂₅=N-, -CH=N-CR₂₅=CH-, -CH=CR₂₄-N=CH-, -N=CR₂₄-CR₂₅=N-, -N=CR₂₄-N=CH-, -CH=CH-O-, -CH=CH-S-, -CH=CH-NR₂₃-;

R₁₇ und R₂₀ unabhängig voneinander für H stehen oder die Bedeutung von R₁₈ haben; eines von R₁₈ und R₁₉ für H steht und das andere von R₁₈ und R₁₉ oder beide ein Substituent sind, ausgewählt unter C₁- bis C₁₈-Alkyl, C₁- bis C₁₈-Alkoxy, C₁- bis C₁₈-Alkylthio, C₁- bis C₁₂-Alkoxy-poly-C₂- bis C₆-oxyalkylen; unsubstituiertem oder mit F, Cl, Br, -CN, C₁- bis C₁₂-Alkyl, C₁- bis C₁₂-Alkoxy, C₁- bis C₁₂-Alkylthio, oder -NR₂₁R₂₂ substituiertem C₅- bis C₈-Cycloalkyl, C₅- bis C₈-Cycloalkoxy, C₅- bis C₈-Cycloalkylthio, C₅- bis C₈-Cycloalkyl-C₁- bis C₄-alkyl, C₅- bis C₈-Cycloalkyl-C₁- bis C₄-alkoxy, C₅- bis C₈-Cycloalkyl-C₁- bis C₄-alkylthio, Phenyl, Phenylthio, Phenyl-C₁- bis C₄-alkyl, Phenyl-C₁- bis C₄-alkoxy, Phenyl-C₁- bis C₄-alkylthio, Phenyl-C₂- bis C₁₂-alkyliden, Phenyl-C(O)-, Phenyl-NR₂₃-C(O)-, Phenyl-NR₂₃-S(O)₂-, Phenyl-S(O)-, Phenyl-S(O)₂-, Phenyl-CO₂-, Phenyl-S(O)-O-, Phenyl-SO₃-, Phenyl-NR₂₃- oder Phenyl-CH=CH-; oder


R₁₇ und R₁₈ gemeinsam, R₁₉ und R₂₀ gemeinsam, oder R₁₇ und R₁₈ gemeinsam und R₁₉ und R₂₀ gemeinsam, oder R₁₈ und R₁₉ gemeinsam ausgewählt sind unter den Gruppen -CH=CR₂₄-CR₂₅=CH-, -N=CR₂₄-CR₂₅=CH-, -CH=CR₂₄-CR₂₅=N-, -CH=N-CR₂₅=CH-, -CH=CR₂₄-N=CH-, -N=CR₂₄-CR₂₅=N-, -N=CR₂₄-N=CH-, -CH=CH-O-, -CH=CH-S-, -CH=CH-NR₂₃-;

R₂₁ und R₂₂ unabhängig voneinander C₁- bis C₂₀-Alkyl, Phenyl, C₁- bis C₁₂-Alkylphenyl, Benzyl oder C₁- bis C₁₂-Alkylbenzyl bedeuten, oder R₂₁ und R₂₂ gemeinsam Tetramethylen, Pentamethylen oder -CH₂CH₂-O-CH₂CH₂- bedeuten;

R₂₃ für H, C₁- bis C₄-Alkyl oder Benzyl steht; und

R₂₄ und R₂₅ unabhängig voneinander H, C₁- bis C₆-Alkyl, C₁- bis C₆-Alkoxy, C₁- bis C₆-Alkylthio, oder F, Cl oder Br bedeuten.


9. Verbindung gemäß Anspruch 8, dadurch gekennzeichnet, dass sie der Formel VI



entspricht, worin

R₁₇ und R₂₀ für H stehen, und R₁₈ und R₁₉ beide C₁- bis C₁₈-Alkyl oder C₁- bis C₁₈-Alkoxy sind, oder R₁₈ und R₁₉ gemeinsam -CH=CR₂₄-CR₂₅=CH- bedeuten; oder R₁₇ und R₁₈ gemeinsam oder R₁₉ und R₂₀ gemeinsam, oder R₁₇ und R₁₈ gemeinsam und R₁₉ und R₂₀ gemeinsam -CH=CR₂₄-CR₂₅=CH- bedeuten, worin R₂₄ und R₂₅ unabhängig voneinander H, F, Cl, C₁- bis C₆-Alkyl oder C₁- bis C₆-Alkoxy sind.

10. Verbindung der Formel VIa,



(VIa)

worin

X₁ für Cl oder Br steht,

eines von R'₁₈ und R'₁₉ oder beide unabhängig voneinander -COOH, oder α- oder α,α-verzweigtes C₃- bis C₂₀-Alkyl oder R_a-C(O)-, worin R_a C₁- bis C₂₀-Alkyl bedeutet; oder C₅- bis C₈-Cycloalkyl, C₅- bis C₈-Cycloalkyl-CH₂-, Phenyl, Benzyl, die unsubstituiert oder substituiert sind mit Halogen, C₁- bis C₁₂-Alkyl oder C₁- bis C₁₂-Alkoxy, bedeuten, oder eines von R'₁₈ und R'₁₉ ein α- oder α,α-verzweigtes C₃- bis C₂₀-Alkyl oder R_a-C(O)-, worin R_a C₁- bis C₂₀-Alkyl bedeutet; oder C₅- bis C₈-Cycloalkyl, C₅- bis C₈-Cycloalkyl-CH₂-, Phenyl, Benzyl, die unsubstituiert oder substituiert sind mit Halogen, C₁- bis C₁₂-Alkyl oder C₁- bis C₁₂-Alkoxy, bedeutet, und das andere von R'₁₈ und R'₁₉ lineares C₁- bis C₁₂-Alkyl ist.

11. Verwendung der Verbindungen V, VI und VIa gemäß den Ansprüchen 8 bis 10 und der Zusammensetzungen gemäß den Ansprüchen 1 oder 2 als organische emittierende Materialien in und für die Herstellung von Elektrolumineszenz ("EL")-Vorrichtungen.


12. Elektrolumineszenz-Vorrichtung, umfassend die Verbindungen V, VI und VIa gemäß den Ansprüchen 8 bis 10 oder die Zusammensetzungen gemäß den Ansprüchen 1 oder 2 als organische emittierende Materialien.

Revendications

1. Composition comprenant (a) une quantité efficace d'un chromophore invité inclus dans une matrice d'un chromophore hôte, ou (b) un chromophore hôte et une quantité efficace d'un chromophore invité tous deux inclus dans une matrice polymère, dans laquelle le spectre d'absorption du chromophore invité recouvre partiellement le spectre d'émission de fluorescence du chromophore hôte, le terme de recouvrement partiel désignant le "recouvrement partiel spectral" défini par l'intégrale suivante :

$$S = \int_0^{+\infty} f_F(v) f_A(v) dv$$


dans laquelle $\int F(v)$ est normalisé, si bien que $\int_0^{+\infty} f_F(v) dv$ est égal au rendement quantique de fluorescence de l'hôte, et dans laquelle v représente le nombre d'onde, $\int F$ le spectre de fluorescence de l'hôte mesuré en quanta, et $\int A$ la répartition spectrale du coefficient d'extinction molaire de l'invité et dans laquelle le chromophore hôte est choisi dans le groupe formé par les benzo[4,5]imidazo[2,1-a]isoindol-11-ones de formule



(V).

dans laquelle

- au plus trois éléments parmi R_{13} , R_{14} , R_{15} et R_{16} représentent chacun un atome d'hydrogène et au moins un élément parmi R_{13} , R_{14} , R_{15} et R_{16} représente un substituant choisi dans le groupe formé par les groupes alkyle en C_1 à C_{18} , alcoxy en C_1 à C_{18} , (alkyle en C_1 à C_{18})thio, (alcoxy en C_1 à C_{12})-polyoxy(alkylène en C_2 à C_6) ; cycloalkyle en C_5 à C_8 , cycloalcoxy en C_5 à C_8 , (cycloalkyle en C_5 à C_8)thio, (cycloalkyle en C_5 à C_8)-(alkyle en C_1 à C_4), (cycloalkyle en C_5 à C_8)-(alcoxy en C_1 à C_4), (cycloalkyle en C_5 à C_8)-(alkyle en C_1 à C_4)thio, phényle, phényloxy, phénylthio, phényl(alkyle en C_1 à C_4), phényl(alcoxy en C_1 à C_4) ou phényl(alkyle en C_1 à C_4)thio non substitué ou substitué par un atome de fluor, de chlore ou de brome, un groupe -CN, alkyle en C_1 à C_{12} , alcoxy en C_1 à C_{12} , (alkyle en C_1 à C_{12})thio, ou $-NR_{21}R_{22}$; ou
- R_{13} et R_{14} ensemble, R_{15} et R_{16} ensemble, ou R_{13} et R_{14} ensemble et R_{15} et R_{16} ensemble, ou R_{14} et R_{15} ensemble sont choisis parmi les groupes $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{CH}=\text{N}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{N}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{CH}=\text{CH}-\text{O}-$, $-\text{CH}=\text{CH}-\text{S}-$, $-\text{CH}=\text{CH}-\text{NR}_{23}-$;
- R_{17} et R_{20} représentent chacun, indépendamment l'un de l'autre, un atome d'hydrogène ou ont la signification de R_{18} ;
- un élément parmi R_{18} et R_{19} représente un atome d'hydrogène et l'autre élément parmi R_{18} et R_{19} ou les deux éléments représentent chacun un substituant choisi dans le groupe formé par un groupe alkyle en C_1 à C_{18} , alcoxy en C_1 à C_{18} , (alkyle en C_1 à C_{18})thio, alcoxy en C_1 à C_{12} -polyoxy(alkylène en C_2 à C_6) ; un groupe cycloalkyle en C_5 à C_8 , cycloalcoxy en C_5 à C_8 , (cycloalkyle en C_5 à C_8)thio, (cycloalkyle en C_5 à C_8)-(alkyle en C_1 à C_4), (cycloalkyle en C_5 à C_8)-(alcoxy en C_1 à C_4), (cycloalkyle en C_5 à C_8)-(alkyle en C_1 à C_4)thio, phényle, phényloxy, phénylthio, phényl(alkyle en C_1 à C_4), phényl(alcoxy en C_1 à C_4), phényl(alkyle en C_1 à C_4)thio, phényl(alkylidène en C_2 à C_{12}), phényl-C(O)-, phényl-NR₂₃-C(O)-, phényl-NR₂₃-S(O)₂-, phényl-S(O)-, phényl-S(O)₂-, phényl-CO₂-, phényl-S(O)-O-, phényl-SO₃-, phényl-NR₂₃- ou phényl-CH=CH- non substitué ou substitué par un atome de fluor, de chlore ou de brome, un groupe -CN, alkyle en C_1 à C_{12} , alcoxy en C_1 à C_{12} , (alkyle en C_1 à C_{12})thio ou $-NR_{21}R_{22}$; ou
- R_{17} et R_{18} ensemble, R_{19} et R_{20} ensemble, ou R_{17} et R_{18} ensemble et R_{19} et R_{20} ensemble, ou R_{18} et R_{19} ensemble sont choisis parmi les groupes $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{CH}=\text{N}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{N}=\text{CR}_{24}-\text{N}=\text{CH}-$; $-\text{CH}=\text{CH}-\text{O}-$, $-\text{CH}=\text{CH}-\text{S}-$, $-\text{CH}=\text{CH}-\text{NR}_{23}-$;
- R_{21} et R_{22} représentent chacun, indépendamment l'un de l'autre, un groupe alkyle en C_1 à C_{20} , phényle, (alkyle en C_1 à C_{12})phényle, benzyle ou (alkyle en C_1 à C_2)benzyle, ou R_{21} et R_{22} forment ensemble un groupe tétraméthylène, pentaméthylène ou $-\text{CH}_2\text{CH}_2-\text{O}-\text{CH}_2\text{CH}_2-$;
- R_{23} représente un atome d'hydrogène, un groupe alkyle en C_1 à C_4 ou un groupe benzyle ; et
- R_{24} et R_{25} représentent chacun, indépendamment l'un de l'autre, un atome d'hydrogène, un groupe alkyle en C_1 à C_6 , alcoxy en C_1 à C_6 , (alkyle en C_1 à C_6)thio, ou un atome de fluor, de chlore ou de brome, ou de formule



(VIa).

dans laquelle

- X_1 représente un atome de chlore ou de brome,
- un élément parmi R'_{18} et R'_{19} ou les deux représentent chacun, indépendamment l'un de l'autre, un groupe -COOH ou alkyle en C_3 à C_{20} à ramification en α ou α,α ou $R_a-\text{C}(\text{O})-$, R_a représentant un groupe alkyle en C_1 à C_{20} ; ou cycloalkyle en C_5 à C_8 , (cycloalkyle en C_5 à C_8)-CH₂-, phényle, benzyle qui est non substitué ou substitué par un atome d'halogène, un groupe alkyle en C_1 à C_{12} ou alcoxy en C_1 à C_{12} , ou

- un élément parmi R'_{18} et R'_{19} représente un groupe alkyle en C_3 à C_{20} à ramification en α ou α,α ou $R_a-C(O)-$, R_a représentant un groupe alkyle en C_1 à C_{20} ; ou cycloalkyle en C_5 à C_8 , (cycloalkyle en C_5 à C_8)- CH_2- , phényle, benzyle qui est non substitué ou substitué par un atome d'halogène, un groupe alkyle en C_1 à C_{12} ou alcoxy en C_1 à C_{12} , et l'autre élément parmi R'_{18} et R'_{19} représente un groupe alkyle en C_1 à C_{12} linéaire, le chromophore invité étant luminescent à l'état moléculaire et étant choisi dans le groupe formé par les quinaclidones, les pérylènes, les perinones, les dicéto- et les dithiocéto-pyrrolopyrroles, les rhodamines, les coumarines, les xanthènes, les oxazines, les oxazoles, les cyanines, les phthalocyanines, les porphyrines, les colorants styryliques, les complexes métalliques et leurs mélanges.

2. Composition selon la revendication 1, **caractérisée en ce que** (a) le chromophore invité est réparti de manière homogène dans la matrice du chromophore hôte, ou (b) le chromophore hôte et le chromophore invité sont tous deux répartis de manière homogène dans la matrice polymère.

3. Procédé de préparation d'une composition selon les revendications 1 ou 2, comprenant un chromophore hôte et un chromophore invité et, si nécessaire, une matrice polymère, le spectre d'absorption du chromophore invité recouvrant partiellement le spectre d'émission de fluorescence du chromophore hôte, **caractérisé par** les étapes consistant à :

(a) choisir le chromophore hôte dans le groupe des benzo[4,5]imidazo[2,1-a]isoindol-11-ones de formule V ou Via,

(b) mélanger le chromophore hôte et une quantité efficace d'au moins un chromophore invité, et éventuellement un polymère ou un précurseur polymérisable, en présence d'un solvant, puis

(c) précipiter les chromophores hôte et invité, éventuellement en présence du polymère de l'étape (b), ou

(d) précipiter les chromophores hôte et invité pendant la polymérisation du précurseur de polymère de l'étape (b).


4. Composition polymérisable comprenant des monomères ou des prépolymères polymérisables mélangés à une composition selon la revendication 1 sous la forme d'une poudre contenant des particules, ou avec des chromophores hôte et invité selon la revendication 1, de préférence dissous dans celle-ci, ou les deux.

5. Composition comprenant une matière support présentant une image à fort relief composée d'une matière photosensible polymérisée, qui contient une composition selon la revendication 1 sous la forme d'une poudre contenant des particules, ou des chromophores hôte et invité selon la revendication 1, ou les deux, si nécessaire dissous et/ou répartis dans celle-ci de manière homogène.

6. Procédé de préparation d'images fluorescentes à fort relief sur un support, **caractérisé par** les étapes consistant à irradier à travers un masque ou à graver au laser la composition photopolymérisable déposée selon la revendication 4, de préférence séchée et dont le solvant a été éliminé, sur le support, à révéler la composition irradiée et enfin à éliminer les parties non irradiées.

7. Utilisation des compositions selon les revendications 1 ou 2 ou des compositions préparées selon la revendication 3, en tant que matières fluorescentes.

8. Composé de formule V




(V).

dans laquelle

- au plus trois éléments parmi R_{13} , R_{14} , R_{15} et R_{16} représentent chacun un atome d'hydrogène et au moins un élément parmi R_{13} , R_{14} , R_{15} et R_{16} représentent chacun un substituant choisi dans le groupe formé par un groupe alkyle en C_1 à C_{18} , alcoxy en C_1 à C_{18} , (alkyle en C_1 à C_{18})thio, (alcoxy en C_1 à C_{12})polyoxy(alkylène en C_2 à C_6) ; un groupe cycloalkyle en C_5 à C_8 , cycloalcoxy en C_5 à C_8 , (cycloalkyle en C_5 à C_8)thio, (cycloalkyle en C_5 à C_8)-(alkyle en C_1 à C_4), (cycloalkyle en C_5 à C_8)-(alcoxy en C_1 à C_4), (cycloalkyle en C_5 à C_8)-(alkyle en C_1 à C_4)thio, phényle, phényloxy, phénylthio, phényl(alkyle en C_1 à C_4), phényl(alcoxy en C_1 à C_4), phényl(alkyle en C_1 à C_4)thio non substitué ou substitué par un atome de fluor, de chlore ou de brome, un groupe -CN, alkyle en C_1 à C_{12} , alcoxy en C_1 à C_{12} , (alkyle en C_1 à C_{12}) thio, ou $-NR_{21}R_{22}$; ou
- R_{13} et R_{14} ensemble, R_{15} et R_{16} ensemble, ou R_{13} et R_{14} ensemble et R_{15} et R_{16} ensemble, ou R_{14} et R_{15} ensemble sont choisis parmi les groupes $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{CH}=\text{N}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{N}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{CH}=\text{CH}-\text{O}-$, $-\text{CH}=\text{CH}-\text{S}-$, $-\text{CH}=\text{CH}-\text{NR}_{23}-$;
- R_{17} et R_{20} représentent chacun, indépendamment l'un de l'autre, un atome d'hydrogène ou ont la signification de R_{18} ;
- un élément parmi R_{18} et R_{19} représente un atome d'hydrogène et l'autre élément parmi R_{18} et R_{19} ou les deux représentent chacun un substituant choisi dans le groupe formé par un groupe alkyle en C_1 à C_{18} , alcoxy en C_1 à C_{18} , (alkyle en C_1 à C_{18})thio, alcoxy en C_1 à C_{12} -polyoxy(alkylène en C_2 à C_6) ; un groupe cycloalkyle en C_5 à C_8 , cycloalcoxy en C_5 à C_8 , (cycloalkyle en C_5 à C_8)thio, (cycloalkyle en C_5 à C_8)-(alkyle en C_1 à C_4), (cycloalkyle en C_5 à C_8)-(alcoxy en C_1 à C_4), (cycloalkyle en C_5 à C_8)-(alkyle en C_1 à C_4)thio, phényle, phényloxy, phénylthio, phényl(alkyle en C_1 à C_4), phényl(alcoxy en C_1 à C_4), phényl(alkyle en C_1 à C_4)thio, phényl(alkylidène en C_2 à C_{12}), phényl-C(O)-, phényl-NR₂₃-C(O)-, phényl-NR₂₃-S(O)₂-, phényl-S(O)-, phényl-S(O)₂-, phényl-CO₂-, phényl-S(O)-O-, phényl-SO₃-, phényl-NR₂₃- ou phényl-CH=CH- non substitué ou substitué par un atome de fluor, de chlore ou de brome, un groupe -CN, alkyle en C_1 à C_{12} , alcoxy en C_1 à C_{12} , (alkyle en C_1 à C_{12})thio ou $-NR_{21}R_{22}$; ou
- R_{17} et R_{18} ensemble, R_{19} et R_{20} ensemble ou R_{17} et R_{18} ensemble et R_{19} et R_{20} ensemble, ou R_{18} et R_{19} ensemble sont choisis parmi les groupes $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{CH}=\text{N}-\text{CR}_{25}=\text{CH}-$, $-\text{CH}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{N}=\text{CR}_{24}-\text{CR}_{25}=\text{N}-$, $-\text{N}=\text{CR}_{24}-\text{N}=\text{CH}-$, $-\text{CH}=\text{CH}-\text{O}-$, $-\text{CH}=\text{CH}-\text{S}-$, $-\text{CH}=\text{CH}-\text{NR}_{23}-$;
- R_{21} et R_{22} représentent chacun, indépendamment l'un de l'autre, un groupe alkyle en C_1 à C_{20} , phényle, (alkyle en C_1 à C_{12})phényle, benzyle ou (alkyle en C_1 à C_2)benzyle, ou R_{21} et R_{22} forment ensemble un groupe tétraméthylène, pentaméthylène ou $-\text{CH}_2\text{CH}_2-\text{O}-\text{CH}_2\text{CH}_2-$;
- R_{23} représente un atome d'hydrogène, un groupe alkyle en C_1 à C_4 ou un groupe benzyle ; et
- R_{24} et R_{25} représentent chacun, indépendamment l'un de l'autre, un atome d'hydrogène, un groupe alkyle en C_1 à C_6 , alcoxy en C_1 à C_6 , (alkyle en C_1 à C_6)thio ou un atome de fluor, de chlore ou de brome.

9. Composé selon la revendication 8, caractérisé en ce qu'il correspond à la formule VI




(VI),

dans laquelle

R_{17} et R_{20} représentent chacun un atome d'hydrogène, et R_{18} ou R_{19} ou les deux représentent chacun un groupe alkyle en C_1 à C_{18} ou alcoxy en C_1 à C_{18} , ou R_{18} et R_{19} forment ensemble un groupe $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$; ou R_{17} et R_{18} ensemble ou R_{19} et R_{20} ensemble, ou R_{17} et R_{18} ensemble et R_{19} et R_{20} ensemble forment un groupe $-\text{CH}=\text{CR}_{24}-\text{CR}_{25}=\text{CH}-$, où R_{24} et R_{25} représentent chacun, indépendamment l'un de l'autre, un atome d'hydrogène, de fluor ou de chlore, un groupe alkyle en C_1 à C_8 ou alcoxy en C_1 à C_8 .

10. Composé de formule VIa



(VIa).

dans laquelle

- X_1 représente un atome de chlore ou de brome,
- un élément parmi R'_{18} et R'_{19} ou les deux, représentent chacun, indépendamment l'un de l'autre, un groupe -COOH ou alkyle en C_3 à C_{20} à ramification en α ou α, α ou $R_a-C(O)-$, R_a représentant un groupe alkyle en C_1 à C_{20} ; ou un groupe cycloalkyle en C_5 à C_8 , (cycloalkyle en C_5 à C_8)- CH_2- , phényle ou benzyle qui est non substitué ou substitué par un atome d'halogène, un groupe alkyle en C_1 à C_{12} ou alcoxy en C_1 à C_{12} , ou
- un élément parmi R'_{18} et R'_{19} représente un groupe alkyle en C_3 à C_{20} à ramification en α ou α, α ou $R_a-C(O)-$, R_a représentant un groupe alkyle en C_1 à C_{20} ; ou un groupe cycloalkyle en C_5 à C_8 , (cycloalkyle en C_5 à C_8)- CH_2- , phényle, benzyle qui est non substitué ou substitué par un atome d'halogène, un groupe alkyle en C_1 à C_{12} ou alcoxy en C_1 à C_{12} , et l'autre élément parmi R'_{18} et R'_{19} représente un groupe alkyle en C_1 à C_{12} linéaire.

11. Utilisation des composés V, VI et VIa selon les revendications 8 à 10 et des compositions selon la revendication 1 ou 2, en tant que matières luminescentes organiques dans et pour la préparation de dispositifs électroluminescents ("EL").

12. Dispositif électroluminescent comprenant les composés V, VI et VIa selon les revendications 8 à 10 ou les compositions selon la revendication 1 ou 2, en tant que matières luminescentes organiques.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.